

Carboxyl Terminated Polyester Resin.**PRELIMINARY VALUES.**

Delivery form: pale granules.

ALBECOR™ 2540 is despatched from our Sant'Albano Stura - Italy production plant.

For further information regarding this product please refer to:

Synthomer Specialty Resins

Phone: +39 0172 658111

eMail: infopowder@synthomer.com

Property	Typical Value	Unit	Method ¹
Acid value	33 - 37	mg KOH/g	Synt. 13/89
Viscosity @200°C (ICI C&P)	2500 - 4000	m Pascal • s	Synt. 21/90
Colour (50% solution)	2 max	Gardner	Synt. 42/93
Other Properties			
Glass transition temper. (Tg)	approx. 62	°C	Synt. 43/93

¹ internal method based upon the specified norm

Application Advice

ALBECOR™ 2540 resin is designed to be used in combination with TGIC in 93:7 ratio for architectural and industrial low temperature cure. The resulting coatings exhibit good flow, excellent flexibility and exterior durability. It gives a good balance between low temperature cure starting from 130°C and blooming free.

Starting Formula:

ALBECOR™ 2540	623
TGIC	47
Ti dioxide	269
Barium Sulphate	47
Flow Agent ²	10
Benzoin	4
	1000

²66%active matter.

Baking Schedule:

10 - 15 minutes at 150°C (object temperature).

Shipping and Storage

ALBECOR™ 2540 resin should be stored in the original, undamaged and unopened containers in a dry place at temperatures between 5 and 30°C. Exposure to direct sunlight should be avoided. Under these conditions, the shelf life of this product is 1 (one) year from the date of delivery. Based on experience, the resin proved stable for an additional 3 (three) years.

Product Safety

Before handling please read the Safety Data Sheet of this product for safety advice, use and disposal.