

Carboxyl Terminated Polyester Resin.**PRELIMINARY VALUE.**

Delivery form: pale granules.

ALBECOR™ 4850 is despatched from our Sant'Albano Stura - Italy production plant.

For further information regarding this product please refer to:

Synthomer Specialty Resins

Phone: +39 0172 658111

eMail: infopowder@synthomer.com

Property	Typical Value	Unit	Method ¹
Acid value	68 - 78	mg KOH/g	Synt. 13/89
Viscosity @200°C (ICI C&P)	1000 - 2000	m Pascal • s	Synt. 21/90
Colour (50%solution)	3 max	Gardner	Synt. 42/93
Other Properties			
Glass transition temper. (Tg)	approx. 56	°C	Synt. 43/93

¹ internal method based upon the specified norm

Application Advice

ALBECOR™ 4850 resin is designed for low temperature cure application starting from 140°C. In combination with suitable epoxy resins (E.E.W. = 700 - 850) in 50/50 ratio, ALBECOR™ 4850 resin offers good mechanical properties, corrosion resistance and overall chemical resistance.

Starting Formula:

ALBECOR™ 4850	296
Epoxy resin	296
Ti dioxide	295
Barium Sulphate	100
Flow Agent ²	9
Benzoin	4
	1000

²66% active matter.

Baking Schedule:

ALBECOR™ 4850 resin provides full cure, depending on formulation and substrate, starting from 15' - 20' at 140°C (object temperature).

Shipping and Storage

ALBECOR™ 4850 resin should be stored in the original, undamaged and unopened containers in a dry place at temperatures between 5 and 30°C. Exposure to sunlight should be avoided. Under these conditions, the shelf life of this product is 1 (one) year from the date of delivery. Based on experience, the resin proved stable for an additional 3 (three) years.

Product Safety

Before handling please read the Safety Data Sheet of this product for advice on safety, use and disposal.