



Revision: 10.11.2025 Page 1 of 1

## Carboxyl Terminated Polyester Additive.

Delivery form: pale granules.

ALBEMAST<sup>™</sup> 9200 is despatched from our Sant'Albano Stura - Italy production plant.

For further information regarding this product please refer to:

Synthomer Specialty Resins

Phone: +39 0172 658111

eMail: infopowder@synthomer.com

Property	Typical Value	Unit	Method <sup>1</sup>
Viscosity @200°C (ICI C&P)	1700 - 2700	m Pascal • s	Synt. 21/90
Colour (50% solution)	2 max	Gardner	Synt. 42/93
Other Properties			
Glass transition temper. (Tg)	approx. 62	°C	Synt. 43/93

<sup>1</sup> internal method based upon the specified norm

## **Application Advice**

ALBEMAST<sup>TM</sup> 9200 is a tribo additive masterbatch suitable to adjust the tribo chargeability of any type of carboxyl powder coating. ALBEMAST<sup>TM</sup> 9200 additive is a carboxyl terminated polyester containing 5% of active matter.

## **Shipping and Storage**

ALBEMAST<sup>TM</sup> 9200 additive should be stored in the original, undamaged and unopened containers in a dry place at temperatures between 5 and 30°C. Exposure to direct sunlight should be avoided. Under these conditions, the shelf life of this product is 1 (one) year from the date of delivery. Based on experience, the resin proved stable for an additional 3 years.

## **Product Safety**

Before handling please read the Safety Data Sheet of this product for advice on safety, use and disposal.