

Carboxyl Terminated Polyester Additive.

Delivery form: pale granules.

ALBEMAST™ 9600 is despatched from our Sant'Albano Stura - Italy production plant.

For further information regarding this product please refer to:

Synthomer Specialty Resins

Phone: +39 0172 658111
eMail: infopowder@synthomer.com

Property	Typical Value	Unit	Method ¹
Acid value	14 - 18	mg KOH/g	Synt. 13/89
Viscosity @200°C (ICI C&P)	1800 - 2600	m Pascal • s	Synt. 21/90
Colour (50% solution)	2 max	Gardner	Synt. 42/93
Other Properties			
Glass transition temper. (Tg)	approx. 56	°C	Synt. 43/93

¹ internal method based upon the specified norm

Application Advice

ALBEMAST™ 9600 additive masterbatch is designed for gloss control in low gloss polyurethane one shot powder coatings formulations based on Albester SilkyMatt™ resins. Small additions on binder raise the gloss of coated film to the desired level.

Shipping and Storage

ALBEMAST™ 9600 additive should be stored in the original, undamaged and unopened containers in a dry place at temperatures between 5 and 30°C. Exposure to direct sunlight should be avoided. Under these conditions, the shelf life of this product is 1 (one) year from the date of delivery. Based on experience, the resin proved stable for an additional 3 (three) years.

Product Safety

Before handling please read the Safety Data Sheet of this product for advice on safety, use and disposal.