ALBEMAST™ 9100

Hydroxyl Terminated Polyester Additive.

Delivery form: pale granules.

ALBEMAST™ 9100 is despatched from our Sant'Albano Stura - Italy production plant.

For further information regarding this product please refer to:

Synthomer Specialty Resins

Phone: +39 0172 658111
eMail: infopowder@synthomer.com

Property	Typical Value	Unit	Method[1]
Hydroxyl value	45 - 55	mg KOH/g	Synt. 12/89
Viscosity @200°C (ICI C&P)	2500 - 4000	m Pascal • s	Synt. 21/90
Colour (50% solution)	2 max	Gardner	Synt. 42/93
Acid value	8 max	mg KOH/g	Synt. 13/89
Other Properties			
Glass transition temper. (Tg)	approx. 51	°C	Synt. 43/93

[1] internal method based upon the specified norm

Application Advice

ALBEMAST™ 9100 is a tribo additive masterbatch suitable to adjust the tribo chargeability of all standard polyester resins. ALBEMAST™ 9100 is a hydroxyl terminated polyester containing 5% of active matter.

Shipping and Storage

ALBEMAST™ 9100 additive should be stored in the original, undamaged and unopened containers in a dry place at temperatures between 5 and 30°C. Exposure to direct sunlight should be avoided. Under these conditions, the shelf life of this product is at least 1 (one) year from the date of delivery. Based on experience the resin proved stability for at least 3 (three) further years. Some agglomeration may occur in bags, this does not affect the performance of the product in the finished coatings.

Product Safety

Before handling please read Safety Data Sheet of this product for advice on safety, use and disposal.

Disclaimer: This information or data and any other advice or recommendations given or made by us (collectively "Information") are not intended to, nor do they, constitute professional advice or services. Information is provided "AS IS" and on an "AS AVAILABLE" basis and without warranty. We do not warrant or accept responsibility for the accuracy, timeliness or completeness of the Information or data or its suitability for a particular purpose. Synthomer makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product. To the maximum extent permitted by applicable law, Synthomer disclaims (i) any and all liability arising out of the application or use of any product (including as to infringement of third party intellectual property rights), (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability. Any Information concerning any possible use or application of Synthomer products is given by us in good faith and it is entirely for you to satisfy yourself fully as to the suitability of Synthomer products for any particular purpose. Synthomer products are sold in accordance with Synthomer's standard terms and conditions of sale which are available from www.synthomer.com/tc.