

**Carboxyl Terminated Polyester Resin.**

Delivery form: pale granules.

ALBESTER™ 5563 is despatched from our Sant'Albano Stura - Italy production plant.

For further information regarding this product please refer to:

Synthomer Specialty Resins

Phone: +39 0172 658111  
eMail: [infopowder@synthomer.com](mailto:infopowder@synthomer.com)

Property	Typical Value	Unit	Method <sup>1</sup>
Acid value	32 - 37	mg KOH/g	Synt. 13/89
Viscosity @200°C (ICI C&P)	2800 - 3600	m Pascal•s	Synt. 21/90
Colour (50% solution)	2 max	Gardner	Synt. 42/93
Other Properties			
Glass transition temper. (Tg)	approx. 61	°C	Synt. 43/93

<sup>1</sup> internal method based upon the specified norm**Application Advice**

ALBESTER™ 5563 resin is a carboxyl terminated polyester resin designed to be used in combination with β-HAA in 95:5 ratio. The resulting coatings exhibit good yellowing resistance, excellent flexibility and ageing, making them perfect for PCM applications.

ALBESTER™ 5563 resin is suitable for GSB Florida 1 year and Qualicoat Class 1 approvals.

Starting Formula:

ALBESTER™ 5563	618
β-HAA	32
Ti dioxide	286
Barium Sulphate	50
Flow Agent <sup>2</sup>	10
Benzoin	4
	1000

<sup>2</sup>66% active matter.

Baking Schedule:

10 minutes at 180°C (object temperature).

**Shipping and Storage**

ALBESTER™ 5563 resin should be stored in the original, undamaged and unopened containers in a dry place at temperatures between 5 and 30°C. Exposure to direct sunlight should be avoided. Under these conditions, the shelf life of this product is 1 (one) year from the date of delivery. Based on experience, the resin proved stable for an additional 3 (three) years.

**Product Safety**

Before handling please read the Safety Data Sheet of this product for advice on safety, use and disposal.

