

Carboxyl Terminated Polyester.

Delivery form: pale granules.

ALBESTER™ 5751 is despatched from our Sant'Albano Stura - Italy production plant.

For further information regarding this product please refer to:

Synthomer Specialty Resins

Phone: +39 0172 658111

eMail: infopowder@synthomer.com

Property	Typical Value	Unit	Method ¹
Acid value	32 - 36	mg KOH/g	Synt. 13/89
Viscosity @200°C (ICI C&P)	2500 - 3500	m Pascal•s	Synt. 21/90
Colour (50% solution)	3 max	Gardner	Synt. 42/93
Other Properties			
Glass transition temper. (Tg)	approx. 59	°C	Synt. 43/93

¹ internal method based upon the specified norm**Application Advice**

ALBESTER™ 5751 resin is designed for combination with β-HAA in 95:5 ratio. The resulting coatings exhibit good flow and yellowing resistance along with excellent flexibility. ALBESTER™ 5751 resin is suitable for GSB Florida 1 year and Qualicoat Class 1 approvals.

Starting Formula:

ALBESTER™ 5751	618
β-HAA	32
Ti dioxide	286
Barium Sulphate	50
Flow Agent ²	10
Benzoin	4
	1000

²66% active matter.

Baking Schedule:

10 minutes at 180°C (object temperature).

15 minutes at 170°C (object temperature).

Shipping and Storage

ALBESTER™ 5751 resin should be stored in the original, undamaged and unopened containers in a dry place at temperatures between 5 and 30°C. Exposure to direct sunlight should be avoided. Under these conditions, the shelf life of this product is 1 (one) year from the date of delivery. Based on experience, the resin proved stable for an additional 3 (three) years.

Product Safety

Before handling please read the Safety Data Sheet of this product for advice on safety, use and disposal.