

Hydroxyl Terminated Polyester Resin.**PRELIMINARY VALUES.**

Delivery form: pale granules.

ALBESTER™ 6310 is despatched from our Sant'Albano Stura - Italy production plant.

For further information regarding this product please refer to:

Synthomer Specialty Resins

Phone: +39 0172 658111

eMail: infopowder@synthomer.com

Property	Typical Value	Unit	Method ¹
Hydroxyl value	105 - 115	mg KOH/g	Synt. 12/89
Acid value	5 max	mg KOH/g	Synt. 13/89
Viscosity @200°C (ICI C&P)	2000 - 3000	m Pascal • s	Synt. 21/90
Colour (50% solution)	2 max	Gardner	Synt. 42/93
Other Properties			
Glass transition temper. (Tg)	approx. 55	°C	Synt. 43/93

¹ internal method based upon the specified norm**Application Advice**

ALBESTER™ 6310 resin, used in combination with non emissive isocyanate curatives, offers excellent stain, detergent and chemical resistance. ALBESTER™ 6310 resin has been specifically designed to give a superior exterior durability.

Starting Formula:

ALBESTER™ 6310	394
Uretdione	194
Ti dioxide	296
Barium Sulphate	105
Flow Agent ²	7
Benzoin	4
	1000

²66% active matter.

Baking Schedule

10 minutes at 200°C (object temperature).

Shipping and Storage

ALBESTER™ 6310 resin should be stored in the original, undamaged and unopened containers in a dry place at temperatures between 5 and 30°C. Exposure to direct sunlight should be avoided. Under these conditions, the shelf life of this product is 1 (one) year from the date of delivery. Based on experience, the resin proved stable for an additional 3 (three) years.

Product Safety

Before handling please read the Safety Data Sheet of this product for safety advice, use and disposal.