

Hydroxyl Terminated Polyester Resin.

Delivery form: pale granules.

ALBESTER SilkyMatt™ 3225 is despatched from our Sant'Albano Stura - Italy production plant.

For further information regarding this product please refer to:

Synthomer Specialty Resins

Phone: +39 0172 658111
eMail: infopowder@synthomer.com

Property	Typical Value	Unit	Method ¹
Hydroxyl value	43 - 53	mg KOH/g	Synt. 12/89
Acid value	4 max	mg KOH/g	Synt. 13/89
Viscosity @200°C (ICI C&P)	4300 - 5300	m Pascal • s	Synt. 21/90
Colour (50% solution)	1 max	Gardner	Synt. 42/93
Other Properties			
Glass transition temper. (Tg)	approx. 57	°C	Synt. 43/93

¹ internal method based upon the specified norm

Application Advice

ALBESTER SilkyMatt™ 3225 resin is a hydroxyl functional resin specifically designed for achieving low gloss in co-extrusion in one shot with ALBESTER SilkyMatt™ 3115 resin and non emissive polyurethane curatives. ALBESTER SilkyMatt™ 3225 resin offers good flexibility, impact resistance and exterior durability. The resulting coatings are particularly suitable for dye-sublimation technique.

Starting Formula:

ALBESTER SilkyMatt™ 3225	504,8
ALBESTER SilkyMatt™ 3115	168
Uretdione	288
Flow Agent ²	10
Benzoin	3
Bayferrox 420 Y	23
Bayferrox 130 M	1
Bayferrox 306 T	2,2
	1000

²66% active matter.

Baking Schedule:

10 minutes at 200°C (object temperature).

Shipping and Storage

ALBESTER SilkyMatt™ 3225 resin should be stored in the original, undamaged and unopened containers in a dry place at temperatures between 5 and 30°C. Exposure to direct sunlight should be avoided. Under these conditions, the shelf life of this product is 1 (one) year from the delivery date. Based on experience, the resin proved stable for an additional 3 (three) years.

Product Safety

Before handling please read the Safety Data Sheet of this product for advice on safety, use and disposal.

Disclaimer: This information or data and any other advice or recommendations given or made by us (collectively "Information") are not intended to, nor do they, constitute professional advice or services. Information is provided "AS IS" and on an "AS AVAILABLE" basis and without warranty. We do not warrant or accept responsibility for the accuracy, timeliness or completeness of the Information or data or its suitability for a particular purpose. Synthomer makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product. To the maximum extent permitted by applicable law, Synthomer disclaims (i) any and all liability arising out of the application or use of any product (including as to infringement of third party intellectual property rights), (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability. Any Information concerning any possible use or application of Synthomer products is given by us in good faith and it is entirely for you to satisfy yourself fully as to the suitability of Synthomer products for any particular purpose. Synthomer products are sold in accordance with Synthomer's standard terms and conditions of sale which are available from www.synthomer.com/tc.

