

Carboxyl Terminated Polyester Resin.

Delivery form: pale granules.

ALBESTER SilkyMatt™ 5549 is despatched from our Sant'Albano Stura - Italy production plant.

For further information regarding this product please refer to:

Synthomer Specialty Resins

Phone: +39 0172 658111
eMail: infopowder@synthomer.com

Property	Typical Value	Unit	Method ¹
Acid value	18 - 22	mg KOH/g	Synt. 13/89
Viscosity @200°C (ICI C&P)	5200 - 6400	m Pascal • s	Synt. 21/90
Colour (50% solution)	2 max	Gardner	Synt. 42/93
Other Properties			
Glass transition temper. (Tg)	approx. 60	°C	Synt. 43/93

¹ internal method based upon the specified norm

Application Advice

ALBESTER SilkyMatt™ 5549 resin is an organo-tin free grade designed for combination with β-HAA in 97:3 ratio. It has been specifically designed for achieving matt finishing by physical blending with coatings based on suitable high reactive resins. The resulting coatings exhibit good flow and good exterior durability, the appearance of the coating is effected by particle size distribution.

Starting Formula:

ALBESTER SilkyMatt™ 5549	617
β-HAA	19
Ti dioxide	300
Barium Sulphate	50
Flow Agent ²	10
Benzoin	4
	1000

²66% active matter.

Baking Schedule:

15 minutes at 180°C (object temperature).

Shipping and Storage

ALBESTER SilkyMatt™ 5549 resin should be stored in the original, undamaged and unopened containers in a dry place at temperatures between 5 and 30°C. Exposure to sunlight should be avoided. Under these conditions, the shelf life of this product is 1 (one) year from the date of delivery. Based on experience, the resin proved stable for an additional 3 (three) years.

Product Safety

Before handling please read the Safety Data Sheet of this product for advice on safety, use and disposal.