

Carboxyl Terminated Polyester Resin.

Delivery form: pale granules.

ALBESTER SilkyMatt™ 6580 is despatched from our Sant'Albano Stura - Italy production plant.

For further information regarding this product please refer to:

Synthomer Specialty Resins

Phone: +39 0172 658111
eMail: infopowder@synthomer.com

Property	Typical Value	Unit	Method ¹
Acid value	56 - 64	mg KOH/g	Synt. 13/89
Viscosity @200°C (ICI C&P)	4400 - 5400	m Pascal • s	Synt. 21/90
Colour (50% solution)	2 max	Gardner	Synt. 42/93
Other Properties			
Glass transition temper. (Tg)	approx. 69	°C	Synt. 43/93

¹ internal method based upon the specified norm

Application Advice

ALBESTER SilkyMatt™ 6580 resin is superdurable, designed for combination with β -HAA in 92:8 ratio. It has been specifically designed for achieving matt finishing by physical blending with coatings based on ALBESTER SilkyMatt™ 6530 resin or ALBESTER SilkyMatt™ 6520 resin. The resulting coatings are suitable GSB Florida 3 years and Qualicoat Class 2.

Starting Formula:

ALBESTER SilkyMatt™ 6580	607
β -HAA	53
Flow Agent ²	16
Barium Sulphate	293
Lancowax PP 1362 D	20
Benzoin	3
Carbon black FW 200	8
	1000

²66% active matter.

Baking Schedule:

10 minutes at 180°C (object temperature).

Shipping and Storage

ALBESTER SilkyMatt™ 6580 resin should be stored in the original, undamaged and unopened containers in a dry place at temperatures between 5 and 30°C. Exposure to direct sunlight should be avoided. Under these conditions, the shelf life of this product is 1 (one) year from the date of delivery. Based on experience, the resin proved stable for an additional 3 (three) years.

Product Safety

Before handling please read the Safety Data Sheet of this product for advice on safety, use and disposal.