

Alcotex 80 is an 80% hydrolysed high molecular weight polyvinyl alcohol which has been specially developed for use as a primary suspending agent for vinyl chloride suspension polymerisation.

For further information regarding this product please refer to:

Stacey Syron

Phone: +44 1279775-329
eMail: Stacey.Syron@synthomer.com

For further information regarding this product please refer to:

Jack Wheatley

Phone: +44 (0) 1279 741 225
eMail: Jack.Wheatley@synthomer.com

Property	Typical Value	Unit	Method ¹
Appearance	White granular solid		
Viscosity @ 20°C, 4% solution	36-42	mPa.s	ATP62
Degree of Hydrolysis	78.5-81.5	mole%	ATP63 & ATP64
Total Solids	> 95.0	%	ATP65
Ash Content	0.5 max.	weight %	ATP66

¹ internal method based upon the specified norm

Application Advice

For detailed information, please contact the Alcotex Technical Service Team at info@synthomer.com

Experience of working closely with PVC manufacturers has contributed to the development of this product.

In listing the advantages of using Alcotex 80, it must be noted that differences in the PVC grade, polymerisation recipe and plant design influence the extent to which any of these benefits are obtained.

The use of Alcotex suspending agents requires no significant plant modification.

The following are advantages, when compared with other 80% hydrolysed polyvinyl alcohol primary suspending agents:-

A) PVC Plant Output and Operating Cost

1. The polymer build-up in the reactor is low, reducing down-time for cleaning.
2. The desired grain size can be achieved using low levels of Alcotex 80.
3. PVC grains of high bulk density are produced.

B) PVC Polymer Quality

1. Alcotex 80 is used to make PVC with a wide range of porosities and bulk densities.
2. The PVC grains made with Alcotex 80 tend to be more spherical such that slightly higher bulk density may be combined with minimum reduction in porosity and with optimum flow characteristics.
3. Plasticiser absorption properties can be adjusted to give fast dry-up times.

Shipping and Storage

1. Alcotex 80 should be stored away from wet areas and naked flames. Ingress of moisture should be avoided to maintain product quality.
2. As supplied, the product should remain fit for use for 24 months from the date of production. Beyond that date, the material may still be fit for use, but we would advise that it is good practice to test the material. As such, we advise that material stored for 12 months or more

after delivery should be tested before use.

3. Aqueous solutions of Alcotex 80 if stored for long periods at elevated temperatures are prone to mould and bacterial attack.

Alcotex 80 is supplied in 20kg (nominal) paper sacks. Each sack carries the grade number, batch number and net weight. Deliveries are palletised with each pallet being stretch wrapped and labelled with the relevant shipping marks.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.