

Alcotex B72 is polyvinyl alcohol which has been specially developed for use as a primary suspending agent for vinyl chloride suspension polymerisation. It is manufactured by Synthomer UK Ltd. using our exclusive manufacturing process which has advantages over other manufacturing methods, in that it allows more efficient control over the degree of hydrolysis and particle size of the product.

For further information regarding this product please refer to:

Stacey Syron

Phone: +44 1279775-329

eMail: Stacey.Syron@synthomer.com

For further information regarding this product please refer to:

Synthomer Alcotex

eMail: Alcotex@synthomer.com

Property	Typical Value	Unit	Method ¹
Appearance	Dark yellow granules/anules		
Ash Content	0.5 max.	% as Na ₂ O	ATP33
Degree of Hydrolysis	72.0-74.0	mole%	ATP10
Total Solids	> 95.0	%	ATP1
Viscosity @ 20°C, 4% solution	5.0-5.8	mPa.s	ATP7

¹ internal method based upon the specified norm

Application Advice

For detailed information, please contact the Alcotex Technical Service team at alcotex@synthomer.com

In listing the advantages of using Alcotex B72, it must be noted that differences in the PVC grade, polymerisation recipe and plant design influence the extent to which any of these benefits are obtained.

Alcotex B72 has been developed to meet the needs of PVC manufacturers who require good grain size control at cost effective concentrations

The principal advantages of using Alcotex B72 can be summarised as follows:

A) PVC Plant Output and Operating Cost

1. The polymer build-up in the reactor is low, reducing down-time for cleaning.
2. The desired grain size can be achieved using low levels of Alcotex B72.
3. PVC grains of good porosity are produced, which facilitates free monomer removal.
4. Alcotex B72 is not prone to dusting.

B) PVC Polymer Quality

1. Alcotex B72 is used to make PVC with a wide range of porosities and bulk densities.
2. The PVC grains made with Alcotex B72 tend to be more spherical such that high porosity may be combined with minimum reduction in bulk density and with optimum flow characteristics.
3. The PVC grain size distribution is narrow, and the levels of over-sized rejects are low.
4. Plasticiser absorption properties can be adjusted to give fast dry-up times.

Disclaimer: This information or data and any other advice or recommendations given or made by us (collectively "Information") are not intended to, nor do they, constitute professional advice or services. Information is provided "AS IS" and on an "AS AVAILABLE" basis and without warranty. We do not warrant or accept responsibility for the accuracy, timeliness or completeness of the Information or data or its suitability for a particular purpose. Synthomer makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product. To the maximum extent permitted by applicable law, Synthomer disclaims (i) any and all liability arising out of the application or use of any product (including as to infringement of third party intellectual property rights), (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability. Any Information concerning any possible use or application of Synthomer products is given by us in good faith and it is entirely for you to satisfy yourself fully as to the suitability of Synthomer products for any particular purpose. Synthomer products are sold in accordance with Synthomer's standard terms and conditions of sale which are available from www.synthomer.com/tc.

5. The "fish-eye" count is low, reducing the reject level in critical applications.

Shipping and Storage

1. Alcotex B72 should be stored away from wet areas. Ingress of moisture should be avoided to maintain product quality.
2. As supplied, the product should remain fit for use for 24 months from the date of production. Beyond that date, the material may still be fit for use, but we would advise that it is good practice to test the material. As such, we advise that material stored for 12 months or more after delivery should be tested before use.
3. Aqueous solutions of Alcotex B72 if stored for long periods at elevated temperatures are prone to mould and bacterial attack.

Alcotex B72 is supplied in 25kg (nominal) plastic sacks and 1000kg big bag. Each pack carries the grade number, batch number and net weight. Deliveries are palletised labelled with the relevant shipping marks.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.