

EMULTEX™ 4030 is an APEO free vinyl acetate acrylic polymer dispersion with a good pigment binding power. It is suitable for formulating premium or general purpose interior coatings for general walls, ceiling, cement fibre board or paneling.

For further information regarding this product please refer to:

Coatings Synthomer

eMail: coatings@synthomer.com

Property	Typical Value	Unit	Method ¹
Total solid content	54 ± 1	%	
pH	4.0 – 5.0		
Viscosity	1,100 – 1,700	cps	Brookfield (3/30 rpm /25°C)
Minimum film forming temperature	14	°C	
Glass transition temperature [Tg]	25	°C	
Particle size	0.35	µm	

¹ internal method based upon the specified norm

Key Advantages

- Colloid stabilized giving good opacity
- Improved wet scrub resistance
- Good all round performance
- Based on non APEO containing surfactants

Shipping and Storage

To ensure maximum stability and maintain optimum polymer dispersion properties, EMULTEX™ 4030 should be stored in closed containers at a temperature between 5°C and 32°C, away from heat sources and direct sunlight. All storage should conform to local fire and building codes.

When properly stored, EMULTEX™ 4030 will remain stable for 6 months from date of delivery.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.