

EMULTEX 4300 is a compounded, polyvinyl alcohol stabilised, vinyl acetate dibutyl maleate copolymer dispersion.

For further information regarding this product please refer to:

Martin Driever

Phone: +49 173 3179751

eMail: [Martin.Driever@synthomer.com](mailto:Martin.Driever@synthomer.com)

Property	Typical Value	Unit	Method <sup>1</sup>
Solids Content	53,0	%	ISO 3251
pH Value	4,5		ISO 976
Viscosity	< 2000	mPa.s	ISO 2255

<sup>1</sup> internal method based upon the specified norm

## Application Advice

EMULTEX 4300 has been designed as binder for the impregnation of polyester and glass fibre fabrics and scrim. After drying, EMULTEX 4300 forms a medium stiff film with good blocking resistance at ambient temperature. At elevated temperatures, the film can be activated and allows sealing of the finished fabrics or scrim to a variety of substrates.

## Shipping and Storage

Store at an even temperature of between +5°C and +35°C avoiding frost and direct sunlight. Stir product before use. If stored according to these conditions and in the original unopened containers, the dispersion will be stable for 6 months following delivery. Product should be used as soon as possible after opening. During processing, storage and transport, avoid any contact with metals (including non-ferrous metals) which are not protected against corrosion. Detailed information is available on request.

## Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.