

# Eastoflex™ P1010PL

## Amorphous Polyolefin



Eastoflex™ Amorphous Polyolefins (APOs) are characteristically saturated, low molecular weight, propylene-based olefin polymers. These products are inherently soft, tacky, and flexible, having a broad compatibility with numerous elastomers, polymers, and tackifying resins. Eastoflex™ APOs are characterized by consistent quality, low odor, good heat stability, and low color. Eastoflex™ P1010PL is a propylene homopolymer, pelletized and coated with a polypropylene powder, having a melt viscosity of 1,000 mPa·s at 190°C.

- Broad compatibility with numerous elastomers, polymers, and tackifying resins
- Broad temperature service range
- Convenient product form
- Excellent thermal and UV stability
- Excellent water and moisture resistance
- Low color
- Low odor

Property	Typical Value	Unit	Method <sup>1</sup>
Ring and Ball Softening Point	155	°C	ASTM E 28, RBSP of pellet coating on formulas ending in "PL" is 163°C. Pellet coating typically 1.5% to 2% by weight
Gardner Color, Molten	1.0		
Penetration Hardness	18	dmm	ASTM D 5
Glass Transition Temperature, Tg	-10	°C	ASTM D 3418
Melt Viscosity at 190°C	1000	cP	ASTM D 3236, Brookfield
Physical Form	Pellets		

<sup>1</sup> internal method based upon the specified norm

## Applications

Caulks and Sealants, Asphalt and Road Construction, Floor polish, Carpet, Additives, Correction fluids, Labels, Tapes, Other coatings, Metal coatings, Waterproofings, Speciality tapes, Other adhesives

## Compatibility and Solubility

Broad compatibility with numerous elastomers, polymers and tackifying resins. Eastoflex™ APOs have shown to be compatible with the following materials: aliphatic tackifying resins, asphalt, butyl rubber, hydrogenated tackifying resins, low density polyethylene, mineral oil, natural rubber, polybutene, polybutylene, polypropylene, polyterpene tackifying resins, and SEBS block copolymers.

## Packaging

- Bags 50-lb net weight (22.7 kg). Pallet of bags 2,250-lb net weight (1020.6 kg). Bags are made of polypropylene.
  - Boxes 50-lb net weight (22.7 kg). Pallet of boxes 900-lb net weight (408.2 kg). Boxes are lined with a low-density polyethylene liner.
- Pellets are coated with polypropylene to minimize blocking.

## Storage

Due to the thermoplastic behavior, pelletized material may fuse, block or lump. This can be accelerated under any of the following

# Eastoflex™ P1010PL

## Amorphous Polyolefin

---



conditions: 1) above ambient temperature, 2) prolonged storage, 3) pressure, e.g., stacking pallets, or a combination of these conditions. For improved handling, we therefore recommend storing the material in a temperature-controlled area, be careful with stacking material or applying pressure and preventing prolonged storage. It is recommended that control of inventory be observed at all times, taking care that the oldest material is used first.

It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted.

### Comments

Properties reported here are typical values. Synthomer makes no representation that the material in any particular shipment will conform exactly to the values given.