

Carboxylated styrene butadiene latex. General purpose polymer binder for paper, paperboard, and nonwovens applications.

For further information regarding this product please refer to:

Consumer Materials

eMail: [consumer.materials@synthomer.com](mailto:consumer.materials@synthomer.com)

Property	Typical Value	Unit	Method <sup>1</sup>
Solids Content	50	%	
pH Value	5,8	-	
Brookfield Viscosity	195	cps	LVT#2, 60 rpm @ 25°C
Glass Transition Temperature Tg	-2	°C	
Surface Tension	36	dynes/cm	
Residue	5	ppm	
Density	8,5	lbs/gal	
Multivalent Ion Stability	Excellent		
Emulsifier	Anionic		
Foaming Tendency	Low		
Odor	Low		
Mechanical Stability	Excellent		

<sup>1</sup> internal method based upon the specified norm

## Application Advice

GenFlo 576 CN general purpose carboxylated styrene-butadiene copolymer is a binder for paper, paperboard, and nonwovens applications.

### Key Advantages

- Excellent film forming features
- Ease of finishing (gloss) and dry pick resistance
- High tensile strength
- Excellent adhesion to a variety of fibers and inorganic particles
- Versatile binder to meet specific needs through compounding with typical crosslinking resins, performance additives, and fillers
- Compatible with conventional application methods used in the paper and nonwovens industry

### End Use Applications

- Binder: Coated Paper and Board, Nonwovens

## Shipping and Storage

### Available Packaging

Disclaimer: This information or data and any other advice or recommendations given or made by us (collectively "Information") are not intended to, nor do they, constitute professional advice or services. Information is provided "AS IS" and on an "AS AVAILABLE" basis and without warranty. We do not warrant or accept responsibility for the accuracy, timeliness or completeness of the Information or data or its suitability for a particular purpose. Synthomer makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product. To the maximum extent permitted by applicable law, Synthomer disclaims (i) any and all liability arising out of the application or use of any product (including as to infringement of third party intellectual property rights), (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability. Any Information concerning any possible use or application of Synthomer products is given by us in good faith and it is entirely for you to satisfy yourself fully as to the suitability of Synthomer products for any particular purpose. Synthomer products are sold in accordance with Synthomer's standard terms and conditions of sale which are available from [www.synthomer.com/tc](http://www.synthomer.com/tc).

- Bulk (Tank Truck)
- Totes (IBC)

Freeze/Thaw Stability: This product is not freeze-thaw stable.

#### Recommended Storage Conditions

- Do not expose product or container to direct sunlight or to freezing temperatures.
- Mix the contents thoroughly before sampling. Product may undergo accelerated thickening with increased heat. Avoid prolonged storage at high temperatures.
- If stored as recommended, product can maintain its quality for the duration of its shelf life.
- Before use, always sample containers that have been stored longer than noted shelf life.
- Store in original packaging.
- Keep container tightly covered when not in use.

Recommended Storage Temperature: 22°C (70°F)

Shelf Life: 6 Months (when stored as recommended)

## Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.