

Impera™ E1780 Hydrocarbon Resin



Impera™ E1780 is a hydrogenated hydrocarbon resin. Impera™ E1780 resin can improve tire performance attributes including rolling resistance, wet grip, and abrasion in tread compounds. Additional performance enhancements can be achieved depending on rubber compound formulation.

For further information regarding this product please refer to:

Synthomer Adhesive Technologies

eMail: Adhesive.Technologies@Synthomer.com

Property	Typical Value	Unit	Method ¹
Softening Point	130	°C	ASTM D 6090
Color, Yellowness Index, 1 cm cell	14		ASTM E 313
Glass transition temperature (DSC Tg-midpoint)	77	°C	ASTM D 3418, 20°C/minute
Density @ 25°C	1.04	g/mL	
Form	Flake		

¹ internal method based upon the specified norm

Applications

Tire components

Handling Precautions

For detailed information on toxicological properties and handling precautions please refer to the current Safety Data Sheet. This information sheet can be downloaded from our web site or requested from the nearest Synthomer office and should be consulted before handling this product.

Packaging

The standard package for Impera™ E1780 hydrocarbon resin is a 44.1-pound (20-kg) multiwall paper bag. Samples (1 kilogram) are available for evaluation.

Storage and Shelf Life

Due to the thermoplastic behavior, pastillated and flaked resins may fuse, block or lump. This can be accelerated under any of the following conditions: 1) above ambient temperature, 2) prolonged storage, 3) pressure, e.g., stacking pallets, or a combination of these conditions. This is particularly applicable for low softening point resin grades. In order to maintain the flake or pastille shape, we therefore recommend storing the material in a temperature-controlled area, be careful with stacking material or applying pressure and preventing prolonged storage. Direct sunlight exposure should be avoided. Synthomer suggests maintaining warehouses below 45°C.

It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted.

Resins are prone to gradual oxidation, some more so than others. This could result in darkening and/or it could have an adverse effect on the solubility of the resin in organic solvents or on its compatibility with polymers. Accordingly, it is recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first.

The shelf life of Impera™ E1780 hydrocarbon resin is 24 months from the date of manufacture, based on the recommended handling and storage conditions. Once the material has surpassed shelf life, please contact us if you would like to receive our suggestions for material re-verification, based on key product characteristics.

Impera™ E1780 Hydrocarbon Resin



Comments

Properties reported here are typical values. Synthomer makes no representation that the material in any particular shipment will conform exactly to the values given.