

KRISTALEX™ 3105SD

Hydrocarbon Resin



KRISTALEX™ 3105SD Hydrocarbon Resin complies with many FDA regulations for applications involving food contact. It is a water-white, highly color stable, nonpolar, low molecular weight thermoplastic polymer with low organic volatile content and excellent thermal and oxidative stability. This resin is compatible with a wide variety of oils, waxes, alkyds, plastics, and elastomers, and is soluble in many common organic solvents. It is indicated for use in adhesives, coatings, and heat seal lacquers. Compliance with a given regulation in a specific situation should be verified prior to use in a food contacting application.

In EVA-based hot melt adhesives KRISTALEX™ 3105SD Hydrocarbon Resin has useful compatibility with EVA grades with up to 30% vinyl acetate and is useful in formulating low-color, low odor adhesives with good low temperature properties. In styrenic block copolymer-based adhesives KRISTALEX™ 3105SD Hydrocarbon Resin preferentially associates with the styrenic end blocks, producing higher room-temperature cohesion without affecting tack and adhesion properties.

- Excellent thermal stability
- Intermediate softening point
- Low odor
- Low organic volatile content
- Made from pure aromatic monomers
- Suitable for use in food contact applications
- Water-white initial color

For further information regarding this product please refer to:

Synthomer Adhesive Technologies

eMail: Adhesive.Technologies@Synthomer.com

Property	Typical Value	Unit	Method ¹
Ring and Ball Softening Point	105	°C	ASTM E 28
Color, Yellowness Index	9		ASTM E 313, 50% solids in toluene
MMAp cloud point	4	°C	from 1:2 mixture of methylcyclohexane and aniline
OMS (odorless mineral spirits) cloud point	58	°C	from Stoddard solvent
Total Organic Volatile Content	<300	ppm	LC
Molecular Weight, Mn	810	g/mol	GPC using polystyrene standards, elution with THF
Molecular Weight, Mw	1440	g/mol	
Molecular Weight, Mz	2420	g/mol	
Polydispersity (Mw/Mn)	1.8		
Melt Viscosity at 105°C	1000	poise	Brookfield
Melt Viscosity at 135°C	100	poise	
Melt Viscosity at 165°C	10	poise	
Melt Viscosity at 205°C	1	poise	
Glass Transition Temperature (T _g -midpoint)	55	°C	DSC, 20°C/minute

Disclaimer: This information or data and any other advice or recommendations given or made by us (collectively "Information") are not intended to, nor do they, constitute professional advice or services. Information is provided "AS IS" and on an "AS AVAILABLE" basis and without warranty. We do not warrant or accept responsibility for the accuracy, timeliness or completeness of the Information or data or its suitability for a particular purpose. Synthomer makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product. To the maximum extent permitted by applicable law, Synthomer disclaims (i) any and all liability arising out of the application or use of any product (including as to infringement of third party intellectual property rights), (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability. Any Information concerning any possible use or application of Synthomer products is given by us in good faith and it is entirely for you to satisfy yourself fully as to the suitability of Synthomer products for any particular purpose. Synthomer products are sold in accordance with Synthomer's standard terms and conditions of sale which are available from www.synthomer.com/tc.

KRISTALEX™ 3105SD

Hydrocarbon Resin



¹ internal method based upon the specified norm

Applications

Adhesives, Automotive, Caulks and Sealants, Labels, Rubber Additives, Packaging Tapes, Tapes

Compatibility and Solubility

Compatible in useful proportions with a wide variety of materials, including styrene-butadiene rubber (SBR) and SBR block copolymers; neoprene, nitrile, polybutadiene, and acrylic polymers; chlorinated rubber; ethylene-vinyl acetate (EVA) resins; styrenated, vinylated, and drying oil alkyds; rosin ester resins; and ethyl hydroxyethyl cellulose (EHEC), as well as modifying the styrenic endblocks of all styrene-containing block copolymers.

Soluble in aliphatic, aromatic, and chlorinate KRISTALEX™ 3105SD Hydrocarbon Resin is soluble in the VOC exempt solvents acetone, methyl acetate, t-butyl acetate (TBA) and perchlorobenzene tetrafluoride (PCBTF) and will tolerate some acetone and/or methyl acetate as a diluent in solvent systems based on TBA and/or PCBTF. VOC exemptions and environmental regulations vary regionally and compliance with local standards should be verified before any claims about VOC content are made.

Packaging

Pastilles in multi-wall paper bags (50 lbs, 22.7 kg net wt).

Storage

Due to the thermoplastic behavior, pastillated and flaked resins may fuse, block or lump. This can be accelerated under any of the following conditions: 1) above ambient temperature 2) prolonged storage 3) pressure, e.g., stacking pallets, or a combination of these conditions. This is particularly applicable for low softening point resin grades. In order to maintain the flake or pastille shape, we therefore recommend storing the material in a temperature-controlled area, be careful with stacking material or applying pressure and preventing prolonged storage. It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted.

Resins are prone to gradual oxidation, some more so than others. This could result in darkening and/or it could have an adverse effect on the solubility of the resin in organic solvents or on its compatibility with polymers. Accordingly, it is recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first.

The useful life of this product can be affected by storage and handling conditions. When stored in the original unopened container in an enclosed area and protected from moisture, extreme temperatures and contamination, the shelf life of this product is estimated to continue to meet applicable sales specifications for 3 years from the date of manufacture. Shelf life is a guide not an absolute value. The product should be reanalyzed for critical properties at the end of its shelf life to see if it meets specification for use.

Comments

Properties reported here are typical of average lots. Synthomer makes no representation that the material in any particular shipment will conform exactly to the values given.