

# KRISTALEX™ F100

## Hydrocarbon Resin

KRISTALEX™ F100 Hydrocarbon Resin is a water-white, color stable, low molecular weight thermoplastic hydrocarbon polymer. Based on purified 8-9 carbon aromatic monomers, this resin is indicated for use in plastics modification, hot melt adhesives and coatings, sealants and caulks. KRISTALEX™ F100 Hydrocarbon Resin is compatible with a wide variety of oils, waxes, alkyds, plastics, and elastomers, and is soluble in many common organic solvents.

In EVA-based hot melt adhesives KRISTALEX™ F100 Hydrocarbon Resin has useful compatibility with EVA grades with up to 30% vinyl acetate and is useful in formulating low-color adhesives with good low temperature properties. In styrenic block copolymer-based adhesives KRISTALEX™ F100 preferentially associates with the styrenic endblocks, producing higher room-temperature cohesion without affecting tack and adhesion properties.

- Excellent thermal stability
- Intermediate softening point
- Made from purified aromatic monomers
- Water-white initial color

For further information regarding this product please refer to:

Synthomer Adhesive Technologies

eMail: [Adhesive.Technologies@Synthomer.com](mailto:Adhesive.Technologies@Synthomer.com)

Property	Typical Value	Unit	Method <sup>1</sup>
Ring and Ball Softening Point	100	°C	ASTM E 28
Color, Hunterlab b	3		uncentrifuged, 5 cm path length, 50% in toluene
OMS (odorless mineral spirits) cloud point	69	°C	from Stoddard solvent
Molecular Weight, Mn	780	g/mol	GPC using polystyrene standards, elution with THF
Molecular Weight, Mw	1290	g/mol	
Molecular Weight, Mz	2060	g/mol	
Polydispersity (Mw/Mn)	1.6		
Melt Viscosity at 120°C	37000	cP	Brookfield
Melt Viscosity at 140°C	3700	cP	
Melt Viscosity at 160°C	760	cP	
Density at 25°C	1.06	kg/dm <sup>3</sup>	
Glass Transition Temperature (Tg-midpoint)	53	°C	DSC, 20°C/minute

<sup>1</sup> internal method based upon the specified norm

## Applications

Adhesives, Assembly, Carpet, Caulks and Sealants, Film Modification, Graphic inks, Hygiene Adhesives, Labels, Other coatings, Plastic Modification, Roofing, Specialty Tapes, Packaging Tapes, Wax Modification, Packaging

# KRISTALEX™ F100

## Hydrocarbon Resin



### Compatibility and Solubility

Compatible at all ratios, or in limited but practically useful proportions, with a wide variety of materials such as styrene-butadiene rubber (SBR) and SBR block copolymers, neoprene, nitrile, polybutadiene, acrylic polymers, chlorinated rubber, EVA resins (ethylenevinyl acetate copolymers), styrenated alkyds, vinylated alkyds, drying oil alkyds, rosin ester resins, as well as modifying the styrenic endblocks of all styrene-containing block copolymers.

Soluble in aliphatic hydrocarbons, aromatic hydrocarbons, chlorinated hydrocarbons, esters and ketones. Insoluble in alcohols, glycols. Limited solubility in nitroparaffins. Solubility Parameters, minimum 20% resin concentration. 7.2-11.1 in Class I solvents - weakly hydrogen-bonded; 6.9-12.6 in Class II solvents - moderately hydrogen-bonded; Insoluble in Class III solvents - strongly hydrogen-bonded.

### Packaging

KRISTALEX™ F100 Hydrocarbon Resin is pastillated and packed in polyethylene bags of 25 kg net and supplied on shrink-wrapped pallets of 40 bags (1000 kg) each, from Synthomer facilities in the Netherlands and from warehouses located in Europe.

### Storage

Due to the thermoplastic behavior, pastillated and flaked resins may fuse, block or lump. This can be accelerated under any of the following conditions: 1) above ambient temperature 2) prolonged storage 3) pressure, e.g., stacking pallets, or a combination of these conditions. This is particularly applicable for low softening point resin grades. In order to maintain the flake or pastille shape, we therefore recommend storing the material in a temperature-controlled area, be careful with stacking material or applying pressure and preventing prolonged storage. It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted.

Resins are prone to gradual oxidation, some more so than others. This could result in darkening and/or it could have an adverse effect on the solubility of the resin in organic solvents or on its compatibility with polymers. Accordingly, it is recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first.

KRISTALEX™ F100 Hydrocarbon Resin material will remain within sales specification for a period of at least 12 months after shipment from Synthomer production facilities in the Netherlands, provided storage conditions outlined in this data sheet are observed. However, as we can neither anticipate the conditions under which the resin is processed nor the end use applications for which it is used, we recommend that the material be tested upon receipt.

### Comments

Properties reported here are typical of average lots. Synthomer makes no representation that the material in any particular shipment will conform exactly to the values given.