

Kristalex™ 3085 Hydrocarbon Resin



Kristalex™ 3085 hydrocarbon resin is a water-white, highly color stable, nonpolar, low molecular weight thermoplastic polymer. This resin is compatible with a wide variety of oils, waxes, alkyds, plastics, and elastomers, and is soluble in many common organic solvents. It is indicated for use in plastics modification, adhesives, coatings, sealants, and caulks.

For further information regarding this product please refer to:

Synthomer Adhesive Technologies

eMail: Adhesive.Technologies@Synthomer.com

In EVA-based hot melt adhesives, Kristalex™ 3085 has useful compatibility with EVA grades with up to 30% vinyl acetate and is useful in formulating low-color adhesives with good low temperature properties. In styrenic block copolymer based adhesives, Kristalex™ 3085 preferentially associates with the styrenic endblocks, producing lower melt viscosity while maintaining room-temperature cohesion without affecting tack and adhesion properties.

- Excellent thermal stability
- Intermediate softening point
- Made from purified aromatic monomers
- Water-white initial color

Property	Typical Value	Unit	Method ¹
Ring and Ball Softening Point	85	°C	ASTM E 28
Color, Yellowness Index	6		ASTM E 313, 50% solids in toluene
MMA cloud point	2	°C	from 1:2 mixture of methylcyclohexane and aniline
OMS (odorless mineral spirits) cloud point	32	°C	from Stoddard solvent
Molecular Weight, Mn	630	g/mol	GPC using polystyrene standards, elution with THF
Molecular Weight, Mw	1100	g/mol	
Molecular Weight, Mz	1790	g/mol	
Polydispersity (Mw/Mn)	1.8		
Melt Viscosity at 100°C	1000	poise	Brookfield
Melt Viscosity at 120°C	100	poise	
Melt Viscosity at 140°C	10	poise	
Melt Viscosity at 160°C	1	poise	
Glass Transition Temperature (Tg-midpoint)	39	°C	DSC, 20°C/minute

¹ internal method based upon the specified norm

Applications

Assembly, Carpet, Caulks and Sealants, Film Modification, Graphics, Labels, Other Construction Applications, Speciality tapes, Tapes, Waterproofings

Compatibility and Solubility

Compatible at all ratios, or in limited but practically useful proportions, with a wide variety of materials, including styrene-butadiene rubber

This information or data including any advice or recommendation(s) provided by us (collectively "Information") are not intended to, nor do they, constitute professional advice or services. Information is provided only as of the date hereof on an "AS IS" and "AS AVAILABLE" basis and we do not warrant the accuracy, timeliness or completeness of the Information. To the maximum extent permitted by applicable law, Synthomer disclaims (i) all implied warranties, including as to continued production, fitness for purpose, non-infringement and merchantability; (ii) all liability arising out of the application or use of any product (including infringement of third party intellectual property rights); and (iii) all liability, including without limitation, for special, indirect or consequential losses. Any Information concerning any possible use or application of Synthomer products is given by us in good faith and it is entirely for the recipient to satisfy itself fully as to the suitability of Synthomer products for any particular purpose. Synthomer products are sold in accordance with Synthomer's standard terms and conditions of sale which are available from www.synthomer.com/tc. Synthomer owns all right, title and interest in the Information and all other intellectual property rights and data associated with this information without limitation. All trademarks and logos are the property of Synthomer. Copyright © 2020 Synthomer, all rights reserved.

Kristalex™ 3085 Hydrocarbon Resin



(SBR) and SBR block copolymers; neoprene, nitrile, polybutadiene, and acrylic polymers; chlorinated rubber; EVA resins (ethylene-vinyl acetate copolymers); styrenated alkyds, vinylated alkyds, drying oil alkyds; rosin resins; and EHEC (ethyl hydroxyethyl cellulose), as well as modifying the styrenic endblocks of all styrene-containing block copolymers.

Soluble in aliphatic, aromatic, and chlorinated hydrocarbons; esters; and ketones. Insoluble in alcohols and glycols. For low or zero VOC systems Kristalex™ 3085 is soluble in the VOC exempt solvents acetone, methyl acetate, t-butyl acetate (TBA) and perchlorobenzene tetrafluoride (PCBTF) and will tolerate some acetone and/or methyl acetate as a diluent in solvent systems based on TBA and/or PCBTF. VOC exemptions and environmental regulations vary regionally and compliance with local standards should be verified before any claims about VOC content are made.

Packaging

Pastilles, in multi-wall paper bags (50 lbs, 22.7 kg net wt).

Storage

Due to the thermoplastic behavior, pastillated and flaked resins may fuse, block or lump. This can be accelerated under any of the following conditions: 1) above ambient temperature 2) prolonged storage 3) pressure, e.g., stacking pallets, or a combination of these conditions. This is particularly applicable for low softening point resin grades. In order to maintain the flake or pastille shape, we therefore recommend storing the material in a temperature-controlled area, be careful with stacking material or applying pressure and preventing prolonged storage. It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted.

Resins are prone to gradual oxidation, some more so than others. This could result in darkening and/or it could have an adverse effect on the solubility of the resin in organic solvents or on its compatibility with polymers. Accordingly, it is recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first.

The useful life of this product can be affected by storage and handling conditions. When stored in the original unopened container in an enclosed area and protected from moisture, extreme temperatures and contamination, the shelf life of this product is estimated to continue to meet applicable sales specifications for 3 years from the date of manufacture. Shelf life is a guide not an absolute value. The product should be reanalyzed for critical properties at the end of its shelf life to see if it meets specification for use.

Comments

Properties reported here are typical of average lots. Synthomer makes no representation that the material in any particular shipment will conform exactly to the values given.