

LIPATON™ SB 29Y57 is a water-based non-ionically stabilised hydrolysis-resistant dispersion of a carboxylated styrene-butadiene copolymer contains an antioxidant, a defoamer and is free from APEOs. This product is compatible with most hydraulic binders.

For further information regarding this product please refer to:

Construction Synthomer

eMail: Construction@synthomer.com

Property	Typical Value	Unit	Method ¹
Total Solids Content	47.0	%	ISO 3251
pH Value	10.0		ISO 976
Viscosity (Brookfield LVF, 60 rpm)	110	mPa·s	ISO 1652

¹ internal method based upon the specified norm

Application Advice

LIPATON™ SB 29Y57 can be used as modification of hydraulic binders in common applications including repair mortar, flooring, rendering, bonding, mineral sealing slurries and as cement based adhesive. LIPATON™ SB 29Y57 is based on APEO free surfactants. This dispersion is free from plasticizers and free from other additives which can migrate.

LIPATON™ SB 29Y57 may show a slight phase separation during storage. Therefore it should be mixed prior to use.

For additional information, please contact our Technical Service team.

Shipping and Storage

LIPATON™ SB 29Y57 must be stored in closed containers between + 5° and + 35°C and protected from frost and direct sunlight. If stored according to these conditions and in the original unopened containers, the dispersion will be stable for 12 months following delivery. However some cream formation cannot be ruled out. It is therefore advisable that the dispersion should be stirred, or mixed before use. Detailed information is available on request. Information on environmental and hazard data may be taken from the material safety data sheet.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.