

LITEX A 25A10 is an anionic, waterbased dispersion of a carboxylated styrene butadiene copolymer.

For further information regarding this product please refer to:

Adhesive Polymers (EMEA)

eMail: Adhesive-polymers-EMEA@synthomer.com

Property	Typical Value	Unit	Method ¹
Solids Content	53.0	%	DIN EN ISO 3251
pH Value	6.0		DIN ISO 976
Viscosity (Brookfield RVT, 20rpm @ 23°C)	250	mPas	DIN ISO 1652
Glass Transition Temperature	14	°C	DIN EN ISO 16805

¹ internal method based upon the specified norm

Application Advice

Above its minimum film formation temperature LITEX A 25A10 dries to form a transparent, compact odourless film.

LITEX A 25A10 is used in many applications where a high adhesion to metallic surfaces is required, e.g. adhesives for the lamination of paper to aluminum foil, either alone or in combination with casein.

LITEX A 25A10 is also suitable in 2-component wood adhesives for D4 applications.

For further information, please refer to the technical service team.

Shipping and Storage

Store at an even temperature of between +5°C and +35°C avoiding frost and direct sunlight. Stir product before use. If stored according to these conditions and in the original unopened containers, the dispersion will be stable for 12 months following delivery. Product should be used as soon as possible after opening. During processing, storage and transport, avoid any contact with metals (including non-ferrous metals) which are not protected against corrosion. Detailed information is available on request.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.