



Revision: 15.05.2025 Page 1 of 1

LITEX LB 422 is a styrene/butadiene copolymer latex used as a binder in the anode of lithium-ion batteries. It offers a good balance of mechanical properties and processability.

For further information regarding this product please refer to:

Katie Cranfield

Phone: +44 7519 120283

eMail: Kathryn.Cranfield@Synthomer.com

Property	Typical Value	Unit	Method <sup>1</sup>
Total Solids Content (TSC)	46	%	ISO 3251
pH-value	7.0		ISO 976
Viscosity	<100	mPa.s	ISO 1652

<sup>1</sup> internal method based upon the specified norm

## **Application Advice**

LITEX LB 422 is a water based carboxylated styrene/butadiene copolymer latex used in the manufacture of the anode electrode of lithium-ion batteries. It is easy to manufacture anode slurries with LITEX LB 422, with the latex resisting gel formation during processing. The binding performance of LITEX LB 422 produces cells with excellent cycle life and electrochemical performance.

Please contact the Synthomer team for further advice on the formulation and use of LITEX LB 422.

## **Key Features**

- High peel strength
- Low rebounce
- Low temperature performance

## **End Use Application**

- EV
- ESS
- 3C

# **Shipping and Storage**

The product must be protected from frost and exposure to direct sunlight. Storage temperatures between +5 °C and +35 °C are recommended. The product contains in-can preservation to protect it against microbiological attack during transportation. For protection against microbiological contamination during storage appropriate plant hygiene is essential. Care must be taken that drums and containers are properly closed. During storage, shipping and handling contact with metal surfaces that are not corrosion protected must be avoided. When stored properly, the product has a shelf life of 6 months from the date of delivery.

Store at a temperature of between +5°C and +35°C avoiding frost and direct sunlight. Stir product before use. If stored according to these conditions and in the original unopened containers, the product will be stable for 6 months following delivery. Product should be used as soon as possible after opening. Detailed information is available on request.

# **Product Safety**

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.