

Litex N 7012N is an aqueous, anionic dispersion of a carboxylated styrene butadiene acrylonitrile copolymer containing a non-staining antioxidant.

For further information regarding this product please refer to:

Martin Driever

Phone: +49 173 3179751

eMail: Martin.Driever@synthomer.com

| Property | Typical Value | Unit | Method ¹ |
|------------------------------|---------------|------|---------------------|
| Solids Content | 41.0 | % | ISO 3251 |
| pH Value | 9,0 | | ISO 976 |
| Viscosity | < 100 | mPas | ISO 1652 |
| Glass Transition Temperature | - 15 | °C | DIN 53765 |
| Particle Size | 150 | nm | |

¹ internal method based upon the specified norm

Application Advice

Litex N 7012N is a medium/soft latex designed for use in a variety of beater addition and wet-end applications. The latex deposits easily on to most fibres, and when added to the stock allows products with good tensile strength, high flexibility and good abrasion resistance to be formed. When used in sufficient quantities Litex N 7012N also imparts excellent resistance to oils, greases and solvents, due to its content of Acrylonitrile.

Shipping and Storage

Store at an even temperature of between +5°C and +35°C avoiding frost and direct sunlight. Stir product before use. If stored according to these conditions and in the original unopened containers, the dispersion will be stable for 12 months following delivery. Product should be used as soon as possible after opening. Detailed information is available on request.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.