


METHYL ACRYLATE, STABILIZED

Acrylic ester used for polymer manufacturing and as a raw material for syntheses.

Molar Mass(g/mol): 86.09

Chemical formula:



Stoichiometric formula: C₄H₆O₂

CAS number: 96-33-3

For further information regarding this product please refer to:

Monomers Sales Synthomer

eMail: monomers@synthomer.com

Property	Typical Value	Unit	Method ¹
Appearance	Clear, colorless liquid	-	Visually
Methyl acrylate	min. 99.85	%	
Methyl acetate	max. 0.045	%	
Methyl propionate	max. 0.06	%	
Alcohols	max. 0.006	%	
Other organic impurities	max. 0.1	%	
Acidity (as Acrylic acid)	max. 0.002	%	ASTM D 1613
Color	max. 5	APHA	ASTM D 1209
Water	max. 0.05	%	ASTM E 1064
Inhibitor (MEHQ) *	0.001 - 0.002	%	ASTM D 3125
Refractive index **	1.402 – 1.404	-	DIN 51 423/ASTM D 1218

¹ internal method based upon the specified norm

* The inhibitor content can be increased above the standard limit as per customer's request

** nD₂₀

Application Advice

Methyl acrylate is used primarily for manufacturing homopolymers and copolymers. Methyl acrylate can be copolymerized for instance with acrylic acid and its salts, esters and acrylamide, with methacrylic acid, methacrylates, acrylonitrile, styrene, maleic acid esters, vinyl acetate, vinyl chloride, butadiene, unsaturated polyesters etc. Methyl acrylate is an important raw material and a starting material for many chemical syntheses.

Parameter	Value, Unit
Appearance, form	Transparent, colorless, clear liquid
Odor	Typical, acrid, penetrating
Boiling point	80 °C
Melting point	(-77) – (-75) °C
Vapour pressure at 0°C	3.08 kPa
Vapour pressure at 20°C	9.05 kPa

Vapour pressure at 50°C	34.0 kPa
Flash point (Closed cup)	(-3) – (-2) °C
Flash point (Open cup)	2 – 3 °C
Explosion limit – upper at 126 °C	19.4 % v/v
Autoignition temperature	415 °C
Heat of evaporation at boiling point	384 kJ / kg
Heat of polymerization	950 kJ / kg
Heat of combustion	22504 kJ / kg
Specific heat of liquid at 20°C	2.01 kJ / kg.K
Density of liquid at 20°C	956 kg / m ³
Vapour density (air=1)	2.9
Coefficient of cubic expansion	1.3 × 10 ⁻³
Refractive index at 20°C	1.402 – 1.404
Viscosity at 0°C	0.63 mPa.s
Viscosity at 20°C	0.49 mPa.s
Surface tension at 20°C	26 mN / m
Solubility ester in water	52 g / l
Solubility water in ester	22.5 g / l
Electrical conductivity	1.1 × 10 ⁵ pS / m

Shipping and Storage

Methyl acrylate is transported in specially equipped railway cars or tanker trucks. Transport containers are filled to a maximum of 91% of their capacity.

In order to prevent spontaneous polymerization, methyl acrylate must always be stored under air, never under inert gases. The air (oxygen) presence is required for a proper functionality of the stabilizer. Product storage temperature must not exceed 35°C. Under these conditions, a storage stability of one year can be expected. It is advisable to minimize the likelihood of methyl acrylate overstorage by a strict observance of the "first-in-first-out" storage principle. For storage periods extended over one month, it is advisable to replenish the dissolved oxygen content in the product by suitable aeration.

Stainless steel or aluminium is the recommended material for storage tanks and piping. Even though methyl acrylate does not corrode carbon steel, there is a risk of product contamination if corrosion occurs. All metal made equipment (tanks, pumps, piping etc.) must be earthed.

All national laws and directives, as well as local regulations governing storage, handling, distribution and disposal of flammable liquids must be strictly observed. Avoid exposure to high temperatures, sparks, flame, light and frost. Keep separated from oxidizing materials. Keep the container tightly closed.

For additional detailed information see the brochure „SAFE HANDLING AND STORAGE OF ACRYLIC ESTERS“, issued by the European Basic Acrylic Monomers Manufacturers Association (EBAM).

Product Safety

Please refer to the Safety Data Sheet for safety information.