

Floor finish, water-based styrene acrylic, polymer emulsion for high traffic applications, such as schools, hospitals and retail.

MOR-GLO™ 8 zinc crosslinked floor finish polymer is used to make premium, well-balanced floor polishes that provide outstanding dirt resistance, reparability, and response to periodic ultra high speed maintenance.

For further information regarding this product please refer to:

Coatings Synthomer

eMail: coatings@synthomer.com

Property	Typical Value	Unit	Method ¹
Solids Content	38.0	%	
pH	8.0		
Viscosity [Brookfield RVT #1/20 rpm @25°C]	<50	cps	
Glass Transition Temperature [Tg]	86	°C	
Density	8.8	lb/gal	
Crosslinking	Zinc crosslinked		

¹ internal method based upon the specified norm

Key Advantages

- Premium performance regardless of maintenance practice
- low odor
- Excellent scuff and black heel mark resistance
- Soil resistance
- Abrasion resistance
- Excellent response to ultra high speed burnishing
- APE-free

Shipping and Storage

This product is supplied in road tankers or in non-returnable plastic drums secured by a lid with clamping ring or in non-returnable palletized bulk containers (net volume 1.000 lt). The product must be protected from frost and exposure to direct sunlight. Storage temperatures between +5 °C and +30 °C (41°F and 95°F) are recommended. The product contains in-can preservation to protect it against microbiological attack during transportation. For protection against microbiological contamination during storage stringent plant hygiene is essential. Depending on the storage conditions addition of suitable preservatives may be necessary. Care must be taken that drums and containers are properly closed. During storage, shipping and handling contact with metal surfaces that are not corrosion protected must be avoided. When stored properly, the product has a shelf life of 12 months from the date of manufacture.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.