

PICCOTAC™ 8090-E

Hydrocarbon Resin

PICCOTAC™ 8090-E hydrocarbon resin is an aromatic-modified, aliphatic hydrocarbon resin developed for the adhesives industry. Its specific degree of modification provides PICCOTAC™ 8090-E with an excellent compatibility with solution and emulsion SBR, SBS, EVA, and many polar elastomers. Due to its low odor and very good thermostability, PICCOTAC™ 8090-E is suggested as tackifying resin for high quality hot melt and hot melt pressure sensitive adhesives. PICCOTAC™ 8090-E is stabilized by addition of antioxidant.

For further information regarding this product please refer to:

Synthomer Adhesive Technologies

eMail: Adhesive.Technologies@Synthomer.com

- Excellent compatibility and performance in styrene block copolymers, natural rubber and SBR
- Light color
- Low odor
- Low softening point, good low temperature properties
- Reduces hot melt coating temperatures of styrenic copolymers

Property	Typical Value	Unit	Method ¹
Ring and Ball Softening Point	91	°C	ASTM E 28
Color, Gardner	4		ASTM D 6166, 50% solids in toluene
MMAp cloud point	65	°C	from 1:2 mixture of methylcyclohexane and aniline
DACP cloud point	20	°C	from 1:1 mixture of xylene and diacetone alcohol
Molecular Weight, Mn	900	g/mol	GPC using polystyrene standards, elution with THF
Molecular Weight, Mw	1700	g/mol	
Molecular Weight, Mz	3500	g/mol	
Polydispersity (Mw/Mn)	1.9		
Glass transition temperature (Tg-midpoint)	38	°C	DSC, 20°C/min

¹ internal method based upon the specified norm

Applications

Adhesives, Carpet, Caulks and Sealants, Labels, Plastic Modification, Roofing, Specialty Tapes, Tapes, Other coatings

Compatibility and Solubility

Compatible at all ratios or in limited but practically useful proportions, with natural and synthetic rubbers, solution and emulsion SBR, EVA (ethylene-vinyl acetate) copolymers, SBS (styrene-butadiene-styrene), SIS (styrene-isoprene-styrene), and SEBS (styrene-ethylene/butylene-styrene) block copolymers block copolymers, APAO (amorphous poly-alpha-olefins), low molecular weight polyethylene, paraffin and microcrystalline waxes.

Soluble at all useful proportions in aliphatic, aromatic and chlorinated hydrocarbons, esters and ethers. Insoluble in alcohols, glycols and water.

Packaging

PICCOTAC™ 8090-E hydrocarbon resin is pastillated and packed in polyethylene bags of 20 kg net, and supplied on shrink wrapped pallets of 50 bags (1000 kg) each, or in big bags of 1000 kgs each, from Synthomer facilities in the Netherlands and from warehouses located in Europe.

PICCOTAC™ 8090-E

Hydrocarbon Resin



Storage

Due to the thermoplastic behavior, pastillated and flaked resins may fuse, block or lump. This can be accelerated under any of the following conditions: 1) above ambient temperature 2) prolonged storage 3) pressure, e.g., stacking pallets, or a combination of these conditions. This is particularly applicable for low softening point resin grades. In order to maintain the flake or pastille shape, we therefore recommend storing the material in a temperature-controlled area; be careful with stacking material or applying pressure and preventing prolonged storage. It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted.

Resins are prone to gradual oxidation, some more so than others. This could result in darkening and/or it could have an adverse effect on the solubility of the resin in organic solvents or on its compatibility with polymers. Accordingly, it is recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first.

Piccotac™ 8090-E hydrocarbon resin material will remain within product specification limits for a period of at least twelve months after shipment from Synthomer's production facilities in the Netherlands, provided storage conditions outlined in this data sheet are observed. However, as we can neither anticipate the conditions under which the resin is processed nor the end use applications for which it is used, we recommend that the material be tested upon receipt.

Comments

Properties reported here are typical of average lots. Synthomer makes no representation that the material in any particular shipment will conform exactly to the values given.