

PLEXTOL W 1078 is a multiphase, self-crosslinking acrylic copolymer dispersion designed for interior use for varnish and stain formulations of parquet and furniture.

For further information regarding this product please refer to:

Dirk Sühling

Phone: +49 2365 49 6796

eMail: dirk.suehling@synthomer.com

Property	Typical Value	Unit	Method ¹
Total Solids	42.0	%	ISO 3251
pH	8.0	-	ISO 976
Viscosity	500	mPa.s	ISO 2555
Minimum Film Forming Temperature (MFFT)	24	°C	
Glass Transition Temperature	35 / 80	°C	

¹ internal method based upon the specified norm

Key Advantages

- Fine particle size
- Excellent hardness development
- Good gloss retention
- Excellent chemical resistance
- Excellent black heel mark resistance
- Good abrasion resistance

Shipping and Storage

This product is supplied in road tankers or in non-returnable plastic drums secured by a lid with clamping ring or in non-returnable palletized bulk containers (net volume 1.000 lt). The product must be protected from frost and exposure to direct sunlight. Storage temperatures between +5 °C and +30 °C are recommended. The product contains in-can preservation to protect it against microbiological attack during transportation. For protection against microbiological contamination during storage stringent plant hygiene is essential. Depending on the storage conditions addition of suitable preservatives may be necessary. Care must be taken that drums and containers are properly closed. During storage, shipping and handling contact with metal surfaces that are not corrosion protected must be avoided. When stored properly, the product has a shelf life of 12 months from the date of delivery.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.