

Pliocryl 4600 is a thermoplastic solvent-based styrene-acrylic copolymer.

It provides extremely fast drying, high hardness and good water resistance properties.

Mainly recommended for traffic marking and floor paints.

For further information regarding this product please refer to:

Teresa Calvo Garcia

Phone: +34 944 711 500

eMail: teresa.calvo@synthomer.com

Property	Typical Value	Unit	Method ¹
Solvent type	Toluene		
Solids Content	50.0	%	ISO 3251
Acid number	7	mg KOH/g SC	ISO 2114
Gardner viscosity @25°C	9.9	Stokes	ASTM D1545
Iodine color	<1	mg/100 ml	DIN 6162
Specific gravity @20°C	0.97	g/cm ³	ISO 2811-1
Flash point	5 (41 °F)	°C	ISO 3679

¹ internal method based upon the specified norm

Key Advantages

- Extremely fast drying
- High hardness and good water resistance
- Good solubility in aromatic solvents, as well as esters and ketones
- Limited solubility in aliphatic hydrocarbons and alcohols

Shipping and Storage

To ensure maximum stability and optimum resin properties, resin should be stored in closed containers at temperature below 25 °C and away from heat sources and sunlight. All storage should conform to local fire and building codes. Metal drums or IBC should be stored away from all sources of flame or combustion. When properly stored, resin will remain stable for 12 months from the date of manufacture.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.