

REGALITE™ C6100L

Hydrocarbon Resin



Regalite™ C6100L Hydrocarbon Resin is a hydrogenated water-white hydrocarbon resin developed derived from petrochemical feedstocks. This resin is especially designed as a component of a multipart tackifier system in hot melt and solvent based pressure sensitive adhesives based on SIS, SBS and SEBS thermoplastic block copolymers, providing superior tack, adhesion and cohesive strength characteristics.

- Excellent heat stability
- Water-white color
- Wide compatibility

For further information regarding this product please refer to:

Synthomer Adhesive Technologies

eMail: Adhesive.Technologies@Synthomer.com

Property	Typical Value	Unit	Method ¹
Ring and Ball Softening Point	95-105	°C	ASTM E 28
Color, Gardner	<1		ASTM D 6166, 50% solids in toluene
Color, Yellowness Index	6-13		ASTM E 313, 2 cm cell, 50% solids in toluene
Weight Loss	2.5	%	5g, 5 hours at 180°C
Viscosity at 180°C	205	mPa.s	Brookfield
Aromatic Hydrogen	>6	%	NMR

¹ internal method based upon the specified norm

Applications

Caulks and Sealants, Roadmarking, Carpet, Additives, Metal coatings, Graphics, Labels, Coatings, Tapes

Compatibility and Solubility

Soluble in aliphatic, aromatic, and chlorinated hydrocarbon solvents. Insoluble in alcohols and water. Compatible in useful proportions with natural and synthetic rubbers, ethylene-vinyl acetate (EVA) copolymers, amorphous polyolefins, paraffin and microcrystalline waxes, ethylene-vinyl acetate (EVA) resins; styrene-butadiene rubber (SBR) copolymer, styrene-ethylene-butylene-styrene (SEBS), styrene-isoprene-styrene (SIS) and styrene-butadiene-styrene (SBS) block copolymers.

Packaging

The standard package for Regaltac C series resins is a 25-kilogram (55.1-pound) multiwall paper bag. Samples (1 kilogram) are available for evaluation.

Storage

Due to the thermoplastic behavior, pastillated and half-ball resins may fuse, block or lump. This can be accelerated under any of the following conditions: 1) above ambient temperature, 2) prolonged storage, 3) pressure, e.g., stacking pallets, or a combination of these conditions. This is particularly applicable for low softening point resin grades. It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted.

When stored in accordance with the MSDS, in it's original unopened container in an enclosed area and protected from moisture, extreme temperatures and contamination, this product (in solid form only) is estimated to continue to meet applicable sales specifications for more than 2 years from the date of manufacture. First in first out inventory control is recommended.