TECHNICAL DATA SHEET

REGALITE™ R1100
Hydrocarbon Resin

REGALITE™ R1100 hydrocarbon resin is a low molecular weight fully hydrogenated, water-white, inert, thermoplastic resin derived from petrochemical feedstocks. This resin is especially designed as tackifier in hot-melt adhesives requiring excellent color retention upon aging.

- Excellent heat and UV stability
- Water-white color
- Wide compatibility

For further information regarding this product please refer to:

Synthomer Adhesive Technologies

eMail: Adhesive.Technologies@Synthomer.com

Property	Typical Value	Unit	Method[1]
Ring and Ball Softening Point	100	°C	ASTM E 28
Color, Hunterlab b	0.3		Uncentrifuged, 5 cm path length, 50% solids in toluene
Density at 25°C	0.99	kg/dm³	
MMAP Cloud Point	80	°C	from 1:2 mixture of methylcyclohexane and aniline
Molecular Weight, Mn	600	g/mol	GPC, using polystyrene standards, elution with THF
Molecular Weight, Mw	830	g/mol	
Molecular Weight, Mz	1160	g/mol	
Polydispersity (Mw/Mn)	1.4		
Melt Viscosity at 120°C	25000	cP	Brookfield
Melt Viscosity at 140°C	2500	cP	
Melt Viscosity at 160°C	500	cP	
Glass Transition Temperature (Tg)	50	°C	DSC, 20°C/minute

[1] internal method based upon the specified norm

Applications

Adhesives, Sealants, Carpet, Packaging, Graphic inks, Hygiene Adhesives, Labels, Polymer Additives, Protective coatings, Specialty Tapes, Tire components

Compatibility and Solubility

Compatible at all ratios, or in limited but practically useful proportions, with natural and synthetic rubbers, EVA (ethylene-vinyl acetate) copolymers, EBA (Ethylene-butylacrylate), APAO (amorphous poly-alpha-olefins), SIS (styrene-isoprene-styrene) block copolymers, SBS (styrene-butadiene-styrene) block copolymers, SIBS (styrene-isoprene/butadiene-styrene) block copolymers, SEBS (styrene-ethylene/butylene- styrene) block copolymers, SEPS (styrene-ethylene/propylene-styrene) block copolymers, polyethylene, polypropylene polymers, PIB (polyisobutene), OBC (olefinic block copolymer), mPE (metallocene catalysed polyethylene), mPP (metallocene catalysed polypropylene), and TPE (thermoplastic elastomers). Soluble at all useful proportions in aliphatic, aromatic, and chlorinated hydrocarbons. Insoluble in alcohols and water.

Packaging

REGALITE™ R1100 hydrocarbon resin is pastillated and packed in polyethylene bags of 20 kg net, and supplied on shrink-wrapped pallets of 50 bags (1000 kg) each, from Synthomer's facilities in the Netherlands and from warehouses located in Europe.

Disclaimer: This information or data and any other advice or recommendations given or made by us (collectively "Information") are not intended to, nor do they, constitute professional advice or services. Information is provided "AS IS" and on an "AS AVAILABLE" basis and without warranty. We do not warrant or accept responsibility for the accuracy, timeliness or completeness of the Information or data or its suitability for a particular purpose. Synthomer makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product. To the maximum extent permitted by applicable law, Synthomer disclaims (i) any and all liability arising out of the application or use of any product (including as to infringement of third party intellectual property rights), (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability. Any Information concerning any possible use or application of Synthomer products is given by us in good faith and it is entirely for you to satisfy yourself fully as to the suitability of Synthomer products for any particular purpose. Synthomer products are sold in accordance with Synthomer's standard terms and conditions of sale which are available from www.synthomer.com/tc.

Storage

Due to the thermoplastic behavior, pastillated and flaked resins may fuse, block or lump. This can be accelerated under any of the following conditions: 1) above ambient temperature 2) prolonged storage 3) pressure, e.g., stacking pallets, or a combination of these conditions. This is particularly applicable for low softening point resin grades. In order to maintain the flake or pastille shape, we therefore recommend storing the material in a temperature-controlled area, be careful with stacking material or applying pressure and preventing prolonged storage.
It should be noted that lumping does not have a negative impact on the product specifications. Due to the nature of the product, claims regarding lumping cannot be accepted. Resins are prone to gradual oxidation, some more so than others. This could result in darkening and/or it could have an adverse effect on the solubility of the resin in organic solvents or on its compatibility with polymers. Accordingly, it is recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first.

Regalite R1100 will remain within product sales specification limits for a period of at least twelve months after shipment from Synthomer production facilities in the Netherlands, provided storage conditions outlined in this data sheet are observed. However, as we can neither anticipate the conditions under which the resin is processed nor the end use applications for which it is used, the product should be reanalyzed for critical properties at the end of its shelf life to determine if it meets specification for use.

Comments

Properties reported here are typical of average lots. Synthomer makes no representation that the material in any particular shipment will conform exactly to the values given.

Disclaimer: This information or data and any other advice or recommendations given or made by us (collectively "Information") are not intended to, nor do they, constitute professional advice or services. Information is provided "AS IS" and on an "AS AVAILABLE" basis and without warranty. We do not warrant or accept responsibility for the accuracy, timeliness or completeness of the Information or data or its suitability for a particular purpose. Synthomer makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product. To the maximum extent permitted by applicable law, Synthomer disclaims (i) any and all liability arising out of the application or use of any product (including as to infringement of third party intellectual property rights), (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability. Any Information concerning any possible use or application of Synthomer products is given by us in good faith and it is entirely for you to satisfy yourself fully as to the suitability of Synthomer products for any particular purpose. Synthomer products are sold in accordance with Synthomer's standard terms and conditions of sale which are available from www.synthomer.com/tc.