

RESINA CT 400 is a medium-oil drying alkyd resin based on tall-oil fatty acids.

RESINA CT 400 is recommended for fast air-drying and forced drying enamels.

The resin contains 40% oil and 37% phthalic anhydride.

Delivery form is 50% in Xylene

For further information regarding this product please refer to:

Teresa Calvo Garcia

Phone: +34 944 711 500

eMail: teresa.calvo@synthomer.com

Property	Typical Value	Unit	Method ¹
Solids content	50.0	%	ISO 3251
Viscosity @25 °C	11.25	Stokes	ASTM D 1545
Acid Number	<12	mg KOH/g SC	ISO 2114
Color Index (Gardner)	<6		ISO 4630
Flash Point	28	°C	ISO 3679
Density (@20 °C)	0.99		ISO 2811-1

¹ internal method based upon the specified norm

Key Advantages

- High gloss
- Fast air drying time
- Good adhesion and mechanical properties

Shipping and Storage

To ensure maximum stability and optimum resin properties, resin should be stored in closed containers at temperature between 5°C and 25°C and away from heat sources and sunlight. All storage should conform to local fire and building codes. Steel drums and IBC should be stored away from all sources of flame or combustion. When properly stored, resin will remain stable for 12 months from the date of manufacture.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.