

RESIPUR™ 9166 is an orthophthalic unsaturated polyester resin of medium reactivity, pre-accelerated and thixotropic. The lower viscosity and gel time makes it suitable for the winter season.

RESIPUR™ 9166 is an opaque pink liquid, free of impurities.

For further information regarding this product please refer to:

Construction Synthomer

eMail: Construction@synthomer.com

Property	Typical Value	Unit	Method ¹
Polymer Content	59	%	ISO 3251
Viscosity @ 25 °C (Brookfield RVT #2/20 rpm)	400	mPa·s	ISO 2555
Gel Time @ 25 °C (2% MEKP at 50 %)	14	min	ASTM D 2471
Thixotropy Index @ 25°C (Brookfield RVT #2/20 rpm @25 °C)	>2.5		ISO 2555
Density @ 20°C	approx. 1.10		ISO 2811-1
Flash Point	approx. 32	°C	ISO 3679
Properties of Cured Resin			
Tensile Strength	63	MPa	ISO 527
Elongation at Break	2.8	%	ISO 527
E-Modulus	3820	MPa	ISO 527
Flexural Strength	115	MPa	ISO 178
Barcol Hardness	49		ASTM D 2583
Shrinkage on Curing	8.9	%	ISO 3521
Water Absorption @ 23 °C (7 days)	0.4	%	ISO 62
HDT	71	°C	ISO 75-A

¹ internal method based upon the specified norm

Application Advice

RESIPUR™ 9166 is designed for use in rigid laminates produced by hand lay-up or spray-up.

RESIPUR™ 9166 may be cured at room temperature by means of the addition of an initiator (e.g. methyl ethyl ketone peroxide - MEKP). In order to improve the surface curing, a solution of paraffin in styrene may be added. To obtain the ideal curing, it is recommended that the molded piece should not be used until 7 days after manufacture. The lamination of consecutive layers with more than 24 hours of interval is not recommended.

The application viscosity may be adjusted through the addition of styrene. The specification data in this technical data sheet is for the unmodified product without addition of styrene.

The delivery form of RESIPUR™ 9166 is approx. 59 % of polymer diluted in styrene.

For additional information, please contact our Technical Service team.

Shipping and Storage

RESIPUR™ 9166 should be stored in the original and unopened containers and in the absence of light for no longer than 3 months at a temperature below 25°C. Higher temperatures may significantly decrease storage stability.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.