

REVACRYL™ DS 2025 is an anionic aqueous emulsion of acrylic ester and styrene copolymer. It is APEO free and does not contain any solvent, or plasticizer.

For further information regarding this product please refer to:

Coatings Synthomer

eMail: coatings@synthomer.com

Property	Typical Value	Unit	Method ¹
Solids content	50.0	%	ISO 3251
pH	8.0		ISO 976
Viscosity (Brookfield RVT)	1050	mPa*s	ISO 2555
MFFT	< 1	°C	internal method
Tg	- 15	°C	internal method

¹ internal method based upon the specified norm

Application Advice

REVACRYL™ DS 2025 is designed for formulating flexible coatings for exterior walls. REVACRYL™ DS 2025 and DS 910 are compatible and can be combined in any proportions to formulate products with a compromise between different properties (flexibility, permeability and resistance to dirt pick-up) to suit varying requirements.

REVACRYL™ DS 2025 is characterised by great flexibility and its lasting mechanical properties.

Shipping and Storage

This product is supplied in road tankers or in non-returnable plastic drums secured by a lid with clamping ring or in non-returnable palletized bulk containers (net volume 1.000 lt). The product must be protected from frost and exposure to direct sunlight. Storage temperatures between +5 °C and +30 °C are recommended. The product contains in-can preservation to protect it against microbiological attack during transportation. For protection against microbiological contamination during storage stringent plant hygiene is essential. Depending on the storage conditions addition of suitable preservatives may be necessary. Care must be taken that drums and containers are properly closed. During storage, shipping and handling contact with metal surfaces that are not corrosion protected must be avoided. When stored properly, the product has a shelf life of 6 months from the date of delivery.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.