

REVACRYL™ L 3752 is an APEO-free, anionic, aqueous styrene-acrylic copolymer dispersion.

For further information regarding this product please refer to:

Coatings Synthomer

eMail: coatings@synthomer.com

Property	Typical Value	Unit	Method ¹
Solids Content	50.0	%	ISO 1625
pH Value	8.0		ISO 976
Viscosity, Brookfield RVT	2050	mPas	ISO 2555
Density	1.04	g/cm ³	ISO 8962
Minimum Film Forming Temperature	18 approx.	°C	ISO 2115
Particle Size	0.1 approx.	µm	Internal method

¹ internal method based upon the specified norm

Application Advice

REVACRYL™ L 3752 is a multi-purpose product suitable for:

- Interior matt paints with high pigment volume concentration
- Silk and gloss paints
- Interior and exterior textured coatings
- Thin and flexible exterior coatings (possible combination with REVACRYL™ DS 2025)

Shipping and Storage

This product is supplied in road tankers or in non-returnable plastic drums secured by a lid with clamping ring or in non-returnable palletized bulk containers (net volume 1.000 lt). The product must be protected from frost and exposure to direct sunlight. Storage temperatures between +5 °C and +30 °C are recommended. The product contains in-can preservation to protect it against microbiological attack during transportation. For protection against microbiological contamination during storage stringent plant hygiene is essential. Depending on the storage conditions addition of suitable preservatives may be necessary. Care must be taken that drums and containers are properly closed. During storage, shipping and handling contact with metal surfaces that are not corrosion protected must be avoided. When stored properly, the product has a shelf life of 6 months from the date of delivery.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.