

REVACRYL R 387 is a surfactant stabilised, acrylic/styrene copolymer dispersion. REVACRYL R 387 is free from APEO.

For further information regarding this product please refer to:

Thomas Fachinger

Phone: +49(0)6181-9880094

eMail: [thomas.fachinger@synthomer.com](mailto:thomas.fachinger@synthomer.com)

Property	Typical Value	Unit	Method <sup>1</sup>
Total Solids	57.0	%	ISO 3251
pH	7.0		ISO 976
Viscosity	1500	mPa.s	ISO 2555
Particle Size	0.25	microns	
Glass Transition Temperature (midpoint)	- 2	°C	

<sup>1</sup> internal method based upon the specified norm

## Application Advice

REVACRYL R 387 has been developed for use in cement based applications such as admixtures and surface patching compounds where flexibility is desirable. REVACRYL R 387 has excellent adhesion to a wide variety of wood, masonry and metal substrates while also showing excellent pigment / filler binding characteristics.

For additional information please contact our technical service team.

## Shipping and Storage

This product is supplied in road tankers or in non-returnable plastic drums secured by a lid with clamping ring or in non-returnable palletized bulk containers (net volume 1.000 lt). The product must be protected from frost and exposure to direct sunlight. Storage temperatures between +5 °C and +30 °C are recommended. The product contains in-can preservation to protect it against microbiological attack during transportation. For protection against microbiological contamination during storage stringent plant hygiene is essential. Depending on the storage conditions addition of suitable preservatives may be necessary. Care must be taken that drums and containers are properly closed. During storage, shipping and handling contact with metal surfaces that are not corrosion protected must be avoided. When stored properly, the product has a shelf life of 12 months from the date of delivery.

## Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.