

REVACRYL™ R 4370 is a styrene-acrylic polymer dispersion based on APEO free surfactants. It has good binding capability to be formulated as a premium or high PVC primer or finish.

For further information regarding this product please refer to:

Coatings Synthomer

eMail: coatings@synthomer.com

Property	Typical Value	Unit	Method ¹
Total solid content	49 ± 1	%	
pH	8 - 9		
Viscosity@ 25 °C - Brookfield #3/60	100 - 600		
Minimum film forming temperature	23	°C	
Glass transition temperature [Tg]	27	°C	

¹ internal method based upon the specified norm

Key Advantages

- Based on APEO free surfactants.
- Does not contain any added formaldehyde or ammonia.
- Good water, alkaline and efflorescence resistance.

Shipping and Storage

To ensure maximum stability and maintain optimum polymer dispersion properties, REVACRYL™ R 4370 should be stored in closed containers at a temperature between 5°C and 32°C, away from heat sources and direct sunlight. All storage should conform to local fire and building codes.

When properly stored, REVACRYL™ R 4370 will remain stable for 6 months from date of delivery.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.