

REVACRYL AE 3020 is an aqueous dispersion of an acrylic ester-styrene copolymer. The dispersion contains an anionic emulsifier system and is free from film forming aids, APEO, solvents and plasticizers.

REVACRYL AE 3020 is a low MFFT silane-modified styrene-acrylic with excellent wet adhesion and water-resistance. It shows high flexibility and is recommended for roof-coatings.

For further information regarding this product please refer to:

Thomas Bernhofer

Phone: +49(0)2365-49-7107

eMail: [thomas.bernhofer@synthomer.com](mailto:thomas.bernhofer@synthomer.com)

Property	Typical Value	Unit	Method <sup>1</sup>
Solids Content	50	%	ISO 3251
pH Value	7,5		ISO 976
Viscosity (23°C, 100 1/s)	250	mPas	ISO 3219
Viscosity (Brookfield RVT 3/20)	2000	mPas	ISO 1652
Glass Transition Temperature	- 2	°C	
Minimum Film Forming Temperature	0	°C	
Ionic Character	Anionic		

<sup>1</sup> internal method based upon the specified norm

## Key Advantages

- Excellent wet adhesion due to silane-modification
- Excellent water-resistance
- High flexibility
- Low MFFT
- Highly recommended for roof-coatings
- Can be formulated without coalescents

## Shipping and Storage

This product is supplied in road tankers or in non-returnable plastic drums secured by a lid with clamping ring or in non-returnable palletized bulk containers (net volume 1.000 lt). The product must be protected from frost and exposure to direct sunlight. Storage temperatures between +5 °C and +30 °C are recommended. The product contains in-can preservation to protect it against microbiological attack during transportation. For protection against microbiological contamination during storage stringent plant hygiene is essential. Depending on the storage conditions addition of suitable preservatives may be necessary. Care must be taken that drums and containers are properly closed. During storage, shipping and handling contact with metal surfaces that are not corrosion protected must be avoided. When stored properly, the product has a shelf life of 12 months from the date of delivery.

## Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.