

REVACRYL R 4389 is a high solids, styrene acrylic polymer dispersion which displays a highly flexible yet water resistant film.

For further information regarding this product please refer to:

Lim Kee Guan

Phone: +603 2080 7231

eMail: keeguan.lim@synthomer.com

Property	Typical Value	Unit	Method ¹
Total Solids Content	57.0	%	
pH	7.0		
Viscosity@ 25 °C - Brookfield #3/30	1200	cps	
Particle Size	0.20	µm	
Minimum Film Forming Temperature	< 0	°C	
Tg	-8	°C	
SG of Dispersion @ 25 °C	1.05		
SG of Polymer @ 25 °C	1.11		

¹ internal method based upon the specified norm

Key Advantages

- High elongation
- Good flexibility at low temperatures

Application Advice

Suitable for joint fillers and caulking compounds.

For additional information please contact our technical service team.

Shipping and Storage

To ensure maximum stability and maintain optimum polymer dispersion properties, REVACRYL R 4389 should be stored in closed containers at a temperature between 5°C and 32°C, away from heat sources and direct sunlight. All storage should conform to local fire and building codes.

When properly stored, REVACRYL R 4389 will remain stable for 6 months from date of delivery.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.