

REVERSOL™ 7330 is a urethane alkyd, modified with soya oil. It has excellent durability, colour and gloss retention.

For further information regarding this product please refer to:

Coatings Synthomer

eMail: coatings@synthomer.com

Property	Typical Value	Unit	Method ¹
Non-Volatile Content	70 ± 1	%	
Viscosity@ 25 degree C	Z3+ to Z4+	Gardner-Holdt	
Specific Gravity @ 25 degree C	0.96-0.98		
Acid Value	13 max	mg KOH/ gm solids	
Colour	8 max	Gardner	
Clarity	Clear, free of particles		
Volatile Content	White Spirit		
Compatibility Long Oil Alkyds	Complete		
Compatibility Medium Oil Alkyds	Limited		
Compatibility Short Oil Alkyds	None		
Composition (non-volatile) Soya oil	59	%	
Solubility White Spirit	Soluble		
Solubility Xylene	Soluble		

¹ internal method based upon the specified norm

Application Advice

Marine enamels. Clear or pigmented wood finishes. Air drying decorative enamels.

Shipping and Storage

To ensure maximum stability and optimum resin properties, resin should be stored in closed containers at temperature below 32°C and away from heat sources and sunlight. All storage should conform to local fire and building codes. Drums should be stored away from all sources of flame or combustion. When properly stored, resin will remain stable for 12 months from the date of production.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.