

REVERSOL™ 7388 L is a urethane alkyd, modified with linoleic rich fatty acid. It has excellent durability, good abrasion resistance, colour retention and alkali resistance. REVERSOL™ 7388 L is thinned down in dearomatised hydrocarbon solvent.

For further information regarding this product please refer to:

Coatings Synthomer

eMail: coatings@synthomer.com

Property	Typical Value	Unit	Method ¹
Non-Volatile Content	55 ± 1	%	
Viscosity@ 25 degree C	9-13	Gardner-Stokes	
Specific Gravity @ 25 degree C	0.92		
Acid Value	2 max	mg KOH/ gm solids	
Colour	5 max	Gardner	
Clarity	Clear to slight hazy, free of particles		
Volatile Content	Dearomatised hydrocarbon		
Compatibility Long Oil Alkyds	Complete		
Compatibility Medium Oil Alkyds	Limited		
Compatibility Short Oil Alkyds	None		
Composition (non-volatile) Linoleic rich fatty acids	60	%	
Solubility White Spirit	Soluble		
Solubility Xylene	Soluble		

¹ internal method based upon the specified norm

Application Advice

Active metal on resin solids: Cobalt % 0.10 Calcium % 0.05 Zirconium %.

Clear wood finishes for flooring. Fast drying enamels.

Shipping and Storage

To ensure maximum stability and optimum resin properties, resin should be stored in closed containers at temperature below 32°C and away from heat sources and sunlight. All storage should conform to local fire and building codes. Drums should be stored away from all sources of flame or combustion. When properly stored, resin will remain stable for 12 months from the date of production.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.