

Regalflex™ E1003 Amorphous Polyolefin



Regalflex™ Amorphous Polyolefins (APOs) are characteristically saturated, low molecular weight, propylene-based olefin polymers. These products are inherently soft, tacky, and flexible, having a broad compatibility with numerous elastomers, polymers, and tackifying resins. Regalflex™ APOs are characterized by consistent quality, low odor, good heat stability, and low color. Regalflex™ E1003 is a copolymer of propylene and ethylene having a melt viscosity of 300 mPa·s at 190°C.

For further information regarding this product please refer to:

Synthomer Adhesive Technologies

eMail: Adhesive.Technologies@Synthomer.com

- Broad compatibility with numerous elastomers, polymers, and tackifying resins
- Broad temperature service range
- Excellent thermal and UV stability
- Excellent water and moisture resistance
- Low color
- Low odor

Property	Typical Value	Unit	Method ¹
Ring and Ball Softening Point	120	°C	ASTM E 28
Gardner Color, Molten	1.0		
Glass Transition Temperature, Tg	-30	°C	ASTM D 3418
Penetration Hardness	100	dmm	ASTM D 5
Melt Viscosity at 190°C	300	cP	ASTM D 3236, Brookfield
Physical Form	Molten/Solid		

¹ internal method based upon the specified norm

Applications

Caulks and Sealants, Asphalt and Road Construction, Automotive, Carpet, Packaging, Film Modification, Labels, Tapes, Other coatings, Plastic Modification, Roadmarking, Roofing, Specialty Tapes, Tapes, Wax Modification, Wire and cable

Compatibility and Solubility

Broad compatibility with numerous elastomers, polymers and tackifying resins. Regalflex™ APOs have shown to be compatible with the following materials: aliphatic tackifying resins, asphalt, butyl rubber, hydrogenated tackifying resins, low density polyethylene, mineral oil, natural rubber, polybutene, polybutylene, polypropylene, polyterpene tackifying resins, and SEBS block copolymers.

Packaging

Regalflex™ E1003 is available in tank trucks or railcars.

Available for blending with other APOs. Blends with E1003 and others APOs can allow for a more convenient product form.

Please be aware that there are additional costs and lead times associated with the made to order package types.

Storage

Molten material should be handled entirely in closed systems blanketed with an inert gas, such as nitrogen. Molten material can be stored satisfactorily under nitrogen in a steel tank at 350°F to 390°F.

Disclaimer: This information or data and any other advice or recommendations given or made by us (collectively "Information") are not intended to, nor do they, constitute professional advice or services. Information is provided "AS IS" and on an "AS AVAILABLE" basis and without warranty. We do not warrant or accept responsibility for the accuracy, timeliness or completeness of the Information or data or its suitability for a particular purpose. Synthomer makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product. To the maximum extent permitted by applicable law, Synthomer disclaims (i) any and all liability arising out of the application or use of any product (including as to infringement of third party intellectual property rights), (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability. Any Information concerning any possible use or application of Synthomer products is given by us in good faith and it is entirely for you to satisfy yourself fully as to the suitability of Synthomer products for any particular purpose. Synthomer products are sold in accordance with Synthomer's standard terms and conditions of sale which are available from www.synthomer.com/tc.

Regalflex™ E1003 Amorphous Polyolefin



Comments

Properties reported here are typical values. Synthomer makes no representation that the material in any particular shipment will conform exactly to the values given.