

Terpolymer designed for elastomeric modification of PVC and plastic goods

For further information regarding this product please refer to:

Consumer Materials

eMail: [consumer.materials@synthomer.com](mailto:consumer.materials@synthomer.com)

Property	Typical Value	Unit	Method <sup>1</sup>
Tg	-19	°C	
Physical Form	off-white powder		
Density	1.10	g/ml	
Average Particle Size	0.5	mm	
Hardness	50	Shore A	

<sup>1</sup> internal method based upon the specified norm

## Application Advice

Sunigum P2100 is an elastomer used for PVC modification that requires good compression set and light color.

### Key Features

- Resistant to heat and UV radiation
- Allow to make low compression set plasticized PVC formulations
- Resistant to oil-based fluids, solvents, animal fats
- Soft touch haptics

### Typical Applications

- Window gaskets

## Shipping and Storage

Available packaging: 20kg bags (poly) & 400kg big bags

The product must be stored in dry, well ventilated area. It is recommended to store in original packaging, away from direct source of heat and sunlight. If stored according to these conditions and in the original unopened containers, the product will be stable for 12 months following manufacturing. Information on environmental and hazard data may be taken from the material safety data sheet.

## Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.