

SYNTHOMER 6628 is an aqueous, colloidal dispersion of carboxylated butadiene-acrylonitrile copolymer with a high acrylonitrile level. The dispersion contains an emulsifier system and is stabilized with an antioxidant.

For further information regarding this product please refer to:

Synthomer Sdn Bhd

Phone: +603-2080 7200

eMail: info.asia@synthomer.com

Property	Typical Value	Unit	Method ¹
Solids Content	45	%	ISO 3251
pH Value	8.2		ISO 976
Viscosity	50	m.Pa.s	ISO 1652
Surface Tension	32	mN/m	ISO 1409
Acrylonitrile Content	High		
Density at 25°C	1.0	g/cm ³	ASTM D1475

¹ internal method based upon the specified norm

Application Advice

SYNTHOMER 6628 is easy to compound with no specific requirements during compounding as the material provides good stabilization. It is easily adaptable to most manufacturing conditions, providing good yield.

SYNTHOMER 6628 is designed for the manufacture of industrial gloves prepared by coagulant dipping. It is soft and flexible and therefore ideal for the production of unsupported gloves; the latex can also be formulated for use as a flock adhesive dip. With the right formulation, gloves made from Synthomer 6628 give good abrasion and puncture resistance with excellent chemical resistance. Our technical service team would be please to provide you with a typical formulation as a guide and assist if needed.

Shipping and Storage

SYNTHOMER 6628 is supplied in road tankers or in non-returnable plastic drums secured by a lid with clamping ring or in non-returnable palletized bulk containers. Store at an even temperature of between +5°C and +35°C, avoiding frost and direct sunlight. Care must be taken that drums and storage containers are closed tightly. During processing, storage and transport of the product, contact with metals, unprotected against corrosion (likewise non ferrous metals), has to be avoided. If stored according to these conditions, in appropriate containers or in bulk condition with proper hygiene management, Synthomer is able to confirm that the latex will be stable for 6 months from production date.

Product Safety

Please refer to the Material Safety Data Sheet for safety and environmental information.