

Synthomer™ Ester Gum 8L-M Resin



Synthomer™ Ester Gum 8L-M Resin is a thermoplastic glycerol ester of gum rosin with very low color and acid number, especially designed to be used in the adhesive industry for the production of hot melt adhesives. The special production process used for this resin permits the production of a product with high oxidation resistance, excellent color retention and minimal odor.

- Good color stability
- Good oxidation resistance
- Low color
- Low odor
- Low acidity
- Medium softening point

For further information regarding this product please refer to:

Synthomer Adhesive Technologies

eMail: Adhesive.Technologies@Synthomer.com

| Property | Typical Value | Unit | Method ¹ |
|-------------------------------|-------------------|----------|-----------------------------------|
| Ring and Ball Softening Point | 84 | °C | ASTM E 28 |
| Color, Gardner | 3 | | ASTM D 6166, 50% solids in xylene |
| Acid Number | 8 | mg KOH/g | ASTM D 465 |
| Appearance | Crystalline Solid | | |
| Description, Base Resin | Rosin | | |

¹ Internal method based upon the specified norm

Applications

Adhesives, Labels, Packaging, Tapes, Wax Modification, Other adhesives

Compatibility and Solubility

Synthomer™ Ester Gum 8L-M is compatible at all ratios, or in limited but practically useful proportions with other resins, waxes and plasticizers; with natural and synthetic rubbers, chlorinated rubber, and ethylcellulose; with EVA (ethylene-vinyl acetate) copolymers and low molecular weight polyethylene; with SIS (styrene-isoprene-styrene) and SBS (styrene-butadiene-styrene) block copolymers; with APAO (amorphous poly-alphaolefins) and other polyolefins; with acrylic resins; with certain polyamide resins and polyurethane compounds; and with PVP (polyvinylpyrrolidone), polyvinylbutyral, nitrocellulose, drying oils and alkyd resins.

Soluble in esters, ketones, higher alcohols, glycol ethers, aliphatic hydrocarbons, aromatic hydrocarbons, chlorinated hydrocarbons. It is insoluble in methanol, ethanol and water.

Packaging

Synthomer™ Ester Gum 8L-M Resin is packaged in polyethylene bags of 25 kgs. net weight, in lumps. It is manufactured and shipped from the Synthomer Mexico site in Uruapan Michoacán, Mexico.

Storage

The form of the product is in small, crushed lumps packaged in a polyethylene bag. Since its softening temperature is relatively low, there is a tendency toward remassing, fusion or agglomeration under conditions of: 1) ambient temperature >30°C; 2) storage near heat sources; 3) prolonged storage; 4) stacking more than 2 pallets high, of any combination of these. Because of the large surface area present in the small particles, the product is susceptible to gradual oxidation which, in severe cases, can cause darkening and/or alteration of the solubility in organic solvents and/or the compatibility with other polymers. For this reason, it is strongly recommended that a strict control of inventory be observed, always using the oldest material first, storing in temperature-controlled conditions, and that stacks be limited to two pallets maximum. Synthomer™ Ester Gum 8L-M is estimated to remain within product Sales Specifications for a period of 6 months from production date if storage conditions outlined in this data sheet are observed. However, as we can neither anticipate the conditions under which the resin is processed nor the end use applications for which is used, we recommend that the

Disclaimer: This information or data and any other advice or recommendations given or made by us (collectively "Information") are not intended to, nor do they, constitute professional advice or services. Information is provided "AS IS" and on an "AS AVAILABLE" basis and without warranty. We do not warrant or accept responsibility for the accuracy, timeliness or completeness of the Information or data or its suitability for a particular purpose. Synthomer makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product. To the maximum extent permitted by applicable law, Synthomer disclaims (i) any and all liability arising out of the application or use of any product (including as to infringement of third party intellectual property rights), (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability. Any Information concerning any possible use or application of Synthomer products is given by us in good faith and it is entirely for you to satisfy yourself fully as to the suitability of Synthomer products for any particular purpose. Synthomer products are sold in accordance with Synthomer's standard terms and conditions of sale which are available from www.synthomer.com/tc.

Synthomer™ Ester Gum 8L-M Resin



Revision: 26.03.2024
Page 2 of 2

material be tested upon receipt.

Comments

Properties reported here are typical of average lots. Synthomer makes no representation that the material in any particular shipment will conform exactly to the values given.