# Tacolyn™ 3570 Resin Dispersion



Revision: 11.04.2022 Page 1 of 2

Tacolyn™ 3570 Resin Dispersion is an anionic, aqueous, solvent-free, and APE (alkylphenol ethoxylate) free dispersion of a stabilized rosin ester. It is designed for use in pressure sensitive adhesives based on acrylic polymer emulsions or carboxylated SBR polymer emulsions, where it greatly enhances the tack and peel to polyethylene and carton board

For further information regarding this product please refer to:

Synthomer Adhesive Technologies

eMail: Adhesive.Technologies@Synthomer.com

- APE-free
- · Broad compatibility
- · Excellent silicone liner wetting
- · Excellent thermal and UV stability
- · Good pigment and substrate wetting
- · Good storage and mechanical stability
- Improves adhesion to polyethylene and polypropylene packaging substrates
- Light color
- Low surface tension
- · Outstanding tackifier in waterborne adhesives
- · Resistance to acids and alkalies

Property	Typical Value	Unit	Method <sup>1</sup>
Particle Size	250	nm	Average particle size
Coarse Particles	0.050	% max	Wt% of particles >45 microns
Ring and Ball Softening Point	67	°C	ASTM E 28, dispersed phase (base resin+emulsifier)
Total solids content	55	%	
рН	7.0		
pH Tolerance Range	4 to 13		
Viscosity at 25°C	250	сР	Brookfield
Density	1.05	g/mL	
Shelf Life	274	days	

<sup>&</sup>lt;sup>1</sup> internal method based upon the specified norm

### **Applications**

Adhesives for construction, Metal coatings, Packaging Speciality, PSA Tapes, Carpet, Flooring Adhesives, Labels, Coatings, Tapes

#### Compatibility and Solubility

Compatible at all ratios, or in limited but useful proportions, with latices and other aqueous systems of natural rubber, SBR, NBR, butadiene, isoprene, butyl, and neoprene synthetic rubbers; polyacrylic emulsions, VA-E (vinyl acetate-ethylene) copolymers and ethylene vinyl acetate-acrylate terpolymers. When strongly alkaline or acidic additives are added to Tacolyn™ 3570 Resin Dispersion, gross localized pH-variations should be avoided, as these can lead to destabilization and grit formation. When mixed with cationic substances, Tacolyn™ 3570 Resin Dispersion may precipitate.

# **Packaging**

Tacolyn™ 3570 Resin Dispersion is supplied in bulk in road tank trucks and in polyethylene semi-bulk containers with a net weight of 1000 kg from Synthomer production facilities in USA. United States facility also has 445# fiber drums available.

Disclaimer: This information or data and any other advice or recommendations given or made by us (collectively "Information") are not intended to, nor do they, constitute professional advice or services. Information is provided "AS IS" and on an "AS AVAILABLE" basis and without warranty. We do not warrant or accept responsibility for the accuracy, timeliness or completeness of the Information or data or its suitability for a particular purpose. Synthomer makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product. To the maximum extent permitted by applicable law, Synthomer disclaims (i) any and all liability arising out of the application or use of any product (including as to infringement of third party intellectual property rights), (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability. Any Information concerning any possible use or application of Synthomer products is given by us in good faith and it is entirely for you to satisfy yourself fully as to the suitability of Synthomer products for any particular purpose. Synthomer products are sold in accordance with Synthomer's standard terms and conditions of sale which are available from www.synthomer.com/tc.

**TECHNICAL DATA SHEET** 

# Tacolyn™ 3570 Resin Dispersion



Revision: 11.04.2022 Page 2 of 2

## **Storage**

The recommended storage temperature range is 50°-100°F. This resin dispersion may be irreparably damaged if frozen. Accordingly, all shipments in cold climate areas are made in insulated or heated carriers. It is recommended that strict control of inventory be observed at all times, taking care that the oldest material is used first.

The useful life of this product can be affected by storage and handling conditions. This dispersion will remain within product specification limits for at least 274 days from date of manufacture from an Synthomer production facility provided that storage conditions are observed.

## **Comments**

Properties reported here are typical of average lots. Synthomer makes no representation that the material in any particular shipment will conform exactly to the values given.