

Emultex P 7252 is a plasticizer-free water-based dispersion based on vinyl acetate and VeoVa (vinyl ester of versatic acid).

Emultex P 7252 is especially suitable for the manufacturing of interior and exterior paints with excellent water, saponification and weathering resistance.

It is also appropriate for the manufacturing of semi-gloss paints.

For further information regarding this product please refer to:

Teresa Calvo Garcia

Tel: +34 944 711 500

eMail: teresa.calvo@synthomer.com

Property	Typical Value	Unit	Method ¹
Solids content	51.0	%	ISO 3251
pH	6.0		ISO 976
Viscosity (Brookfield RVT #1/20 @23 °C)	90	mPas	ISO 2555
Minimum Film Forming Temperature	approx. 16	°C	ISO 2115
Glass Transition Temperature	approx. 34	°C	ISO 11357-3

¹ internal method based upon the specified norm

Key Advantages

- Excellent water and saponification resistance
- Exceptionally high binding power
- High blocking resistance
- Excellent weathering resistance

Shipping and Storage

This product is supplied in road tankers or in non-returnable plastic drums secured by a lid with clamping ring or in non-returnable palletized bulk containers (net volume 1.000 lt). The product must be protected from frost and exposure to direct sunlight. Storage temperatures between +5 °C and +30 °C are recommended. The product contains in-can preservation to protect it against microbiological attack during transportation. For protection against microbiological contamination during storage stringent plant hygiene is essential. Depending on the storage conditions addition of suitable preservatives may be necessary. Care must be taken that drums and containers are properly closed. During storage, shipping and handling contact with metal surfaces that are not corrosion protected must be avoided. When stored properly, the product has a shelf life of 6 months from the date of delivery.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.