

PLEXTOL DV 245 is an aqueous emulsion of a self-crosslinking acrylic polymer.

For further information regarding this product please refer to:

Daniele Zimmermann

Tel: +49 176 116 60850

eMail: daniele.zimmermann@synthomer.com

Property	Typical Value	Unit	Method <sup>1</sup>
Solids Content	55.0	%	ISO 3251
pH Value	2.5		DIN ISO 976
Viscosity	< 500	mPa s	ISO 1652
Glass Transition Temperature	- 33	°C	DIN 53765
Mean Particle Size	approx. 0.33	µm	
Density	1.04	g/cm <sup>3</sup>	DIN 51757
Tensile Strength	2	N/mm <sup>2</sup>	DIN EN ISO 527
Elongation at Break	140	%	DIN EN ISO 527
Minimum Film-Forming Temperature	< 0	°C	DIN ISO 2115

<sup>1</sup> internal method based upon the specified norm

## Application Advice

### Applications

- Boilproof and dry-cleanable finishing, coating and lamination of textiles and non-wovens.
- Bonding of webs, particularly for manufacturing interlinings
- Non-slip paper coating.
- Cohesive blend component

### Film properties

Evaporation of the water above the minimum film-forming temperature leaves a clear, colourless film. In order to obtain complete crosslinkage, additional heat treatment is required. We recommend 5 min at 140 °C for a film on which physical or chemical tests are to be performed. The crosslinked film is very soft, extensible and slightly tacky at room temperature. It is insoluble in water and resistant to many acids and alkalis. It is virtually insoluble in organic solvents. Particularly noteworthy is its good lightfastness and resistance to weathering and ageing.

### Instruction for use

PLEXTOL DV 245 can be diluted with water to provide spraying and impregnating liquors of any desired concentration. These liquors can be foamed by mixing in air. For impregnation by means of foam, we recommend the addition of Marlupal 013/109 (approx. 2 g/l) as a foaming agent and ROHAGIT SD 25 (approx. 10 g/l) as a foam stabiliser. For coatings on a foam base, we suggest ammonium stearate as a foaming agent. PLEXTOL DV 245 can be thickened by means of thickener emulsions (e. g. ROHAGIT SD 15), thickener solutions (e. g. ROHAGIT SD 25) and cellulose or starch derivatives to provide printing, nip-padding and coating mpounds. The drying process must guarantee adequate crosslinkage of the polymer, i. e. after evaporation of the water, the material must reach a temperature between 130 and 160 °C for a short period. The crosslinkage reaction is catalysed by acid and can be accelerated by adding phosphoric acid or p-toluene sulphonic acid (approx. 10 g/l of a 10 % solution on emulsion). By mixing PLEXTOL DV 245 with other emulsions from the PLEXTOL range, the film properties of the foamer can be influenced within wide limits and thus adapted to the intended application.

## Shipping and Storage

This product is supplied in road tankers or in non-returnable plastic drums secured by a lid with clamping ring or in non-returnable palletized bulk containers (net volume 1.000 lt). The product must be protected from frost and exposure to direct sunlight. Storage temperatures between +5 °C and +30 °C are recommended. The product contains in-can preservation to protect it against microbiological attack during transportation. For protection against microbiological contamination during storage stringent plant hygiene is essential. Depending on the storage conditions addition of suitable preservatives may be necessary. Care must be taken that drums and containers are properly closed. During storage, shipping and handling contact with metal surfaces that are not corrosion protected must be avoided. When stored properly, the product has a shelf life of 12 months from the date of delivery.

## Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.