

Pliolak AF 522 is a Solvent-based medium-oil alkyd resin for decorative coatings, industrial primers and enamels

The resin contains 52% oil and 28% phthalic anhydrid.

Delivery form 60% in D40

For further information regarding this product please refer to:

Teresa Calvo Garcia

Tel: +34 944 711 500

eMail: teresa.calvo@synthomer.com

Property	Typical Value	Unit	Method ¹
Solids content	60	%	ISO 3251
Viscosity (Gardner @25 °C)	49.8	Stokes	ASTM D 1545
Acid Value	<12	mg KOH/g SC	ISO 2114
Color Index (Gardner)	<10		ISO 4630
Flash Point	32	°C	ISO 3679
Density (@20 °C)	0.94		ISO 2811-1

¹ internal method based upon the specified norm

Key Advantages

- Excellent drying time
- High hardness
- Good yellowing and weather resistance
- Compatible with most long-oil alkyd resins
- VOC 2010 compliant

Shipping and Storage

To ensure maximum stability and optimum resin properties, resin should be stored in closed containers at temperature between 5°C and 25°C and away from heat sources and sunlight. All storage should conform to local fire and building codes. Steel drums and IBC should be stored away from all sources of flame or combustion. When properly stored, resin will remain stable for 12 months from the date of manufacture.

Product Safety

Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.